

ZENITE® 5244L

Liquid Crystal Polymer

Zenite 5244L is a 40% glass/mineral reinforced LCP resin with improved toughness.

Product information

Resin Identification	LCP-(GF+MD)4 0	ISO 1043
Part Marking Code	>LCP-(GF+MD)40<	ISO 11469

Rheological properties

Moulding shrinkage, parallel	0.1 %	ISO 294-4, 2577
Moulding shrinkage, normal	0.4 %	ISO 294-4, 2577

Typical mechanical properties

Tensile modulus	14000 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	131 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	1.7 %	ISO 527-1/-2
Flexural modulus	13100 MPa	ISO 178
Flexural strength	200 MPa	ISO 178
Charpy impact strength, 23°C	27 kJ/m²	ISO 179/1eU
Charpy notched impact strength, 23°C	16.6 kJ/m²	ISO 179/1eA
Izod impact strength, 23°C	28 kJ/m²	ISO 180/1U
Poisson's ratio	0.33 ^[C]	

[C]: Calculated

Thermal properties

Melting temperature, 10°C/min	318 °C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	285 °C	ISO 75-1/-2
Coefficient of linear thermal expansion (CLTE), parallel	6 E-6/K	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	48 E-6/K	ISO 11359-1/-2

Flammability

Burning Behav. at 1.5mm nom. thickn.	V-0 class	IEC 60695-11-10
Thickness tested	1.5 mm	IEC 60695-11-10
Burning Behav. at thickness h	V-0 class	IEC 60695-11-10
Thickness tested	0.8 mm	IEC 60695-11-10
UL recognition	yes	UL 94

Physical/Other properties

Density	1710 kg/m³	ISO 1183
---------	------------	----------

Injection

Drying Recommended	yes
Drying Temperature	150 °C
Drying Time, Dehumidified Dryer	4 - 6 h
Processing Moisture Content	≤0.01 %
Melt Temperature Optimum	335 °C

ZENITE® 5244L

Liquid Crystal Polymer

Min. melt temperature	325 °C
Max. melt temperature	350 °C
Screw tangential speed	0.2 - 0.3 m/s
Mold Temperature Optimum	100 °C
Min. mould temperature	80 °C
Max. mould temperature	120 °C
Back pressure	3 MPa
Ejection temperature	285 °C

Characteristics

Processing	Injection Moulding
Special characteristics	Flame retardant, Heat stabilised or stable to heat, High Flow, Low Warpage, Lead-free soldering resistant
