

AT[®] 525

AT[®]

Product information

Resin Identification	(PE-LD)	ISO 1043
Part Marking Code	>(PE-LD)<	ISO 11469
Vinyl acetate content	0 %	

Rheological properties

Melt Flow Index	0.8 g/10min	ASTM D 1238
Temperature	190 °C	
Load	2.16 kg	

Physical/Other properties

Density	922 kg/m ³	
---------	-----------------------	--

Film Properties

Stress at yield, machine direction, 500 mm/min	13 MPa	ASTM D 882
Stress at yield, transverse, 500 mm/min	13 MPa	ASTM D 882
Maximum stress, machine direction, 500 mm/min	29 MPa	ASTM D 882
Maximum stress, transverse, 500 mm/min	22 MPa	ASTM D 882
Maximum strain, machine direction, 500 mm/min	400 %	ASTM D 882
Maximum strain, transverse, 500 mm/min	610 %	ASTM D 882
Gloss, 45°	50	ASTM D 2457
Haze	9	ASTM D 1003