

AT[®] 7205

Product information

Vinyl acetate content %

Rheological properties

Melt Flow Index	0.3 g/10min	ASTM D 1238
Temperature	190 °C	
Load	2.16 kg	

Typical mechanical properties

Tensile Strength	20 MPa	ASTM D 638
Elongation at break	610 %	ASTM D 638
Flexural Modulus	270 MPa	ASTM D 790
Shore A hardness	97	ASTM D 2240
Shore D hardness	52	ASTM D 2240

Thermal properties

Vicat softening temperature, 50°C/h 10N	101 °C	ISO 306
---	--------	---------

Other properties

Density	924 kg/m ³
---------	-----------------------