

NILAMID XS3 GF40 NC 1102/V - PA*

Description

Semi-aromatic polyamide blend, 40% glass fibre

XS compounds are designed for injection molding of parts with a high standard of technical requirements. The most relevant characteristics are the following: High stiffness and strength; small influence on mechanical properties after water uptake Good creep behavior Excellent surface finish

Good dimensional stability Low warpage

Physical properties	dry / cond	Unit	Test Standard
Density	91.8 / -	lb/ft ³	ISO 1183
Molding shrinkage, parallel	0.1	%	ISO 294-4, 2577
Molding shrinkage, normal	0.5	%	ISO 294-4, 2577
Water absorption, 23°C-sat	4.6 / *	%	ISO 62
Humidity absorption, 23°C/50%RH	0.8 / *	%	ISO 62

Mechanical properties	dry / cond	Unit	Test Standard
Tensile modulus	1.96E6 / 1.81E6	psi	ISO 527-2/1A
Tensile stress at break, 5mm/min	31900 / 27600	psi	ISO 527-2/1A
Tensile strain at break, 5mm/min	3.5 / 4	%	ISO 527-2/1A
Flexural modulus, 23°C	1.67E6 / 1.54E6	psi	ISO 178
Flexural stress at max. force	49300 / 40600	psi	ISO 178
Charpy impact strength, 23°C	45.2 / 42.8	ft-lb/in ²	ISO 179/1eU
Charpy impact strength, -30°C	35.7 / -	ft-lb/in ²	ISO 179/1eU
Charpy notched impact strength, 23°C	5.95 / 6.18	ft-lb/in ²	ISO 179/1eA
Charpy notched impact strength, -30°C	4.99 / -	ft-lb/in ²	ISO 179/1eA
Izod impact notched, 23°C	6.18 / 6.66	ft-lb/in ²	ISO 180/1A

Thermal properties	dry / cond	Unit	Test Standard
Melting point, peak	500	°F	ISO 3146
DTUL at 1.8 MPa	446 / *	°F	ISO 75-1, -2
Flammability @3.2mm nom. thickn.	HB / *	class	UL 94
Flammability @1.6mm nom. thickn.	HB / *	class	UL 94
Flammability @0.8mm nom. thickn.	HB / *	class	UL 94
UL recognition (0.4)	UL / *	-	UL 94
Continuous service temperature	120 / *	°C	DIN/IEC 60216-1

Electrical properties	dry / cond	Unit	Test Standard
Volume resistivity	1E12 / -	Ohm*m	IEC 60093
Surface resistivity	1E13 / -	Ohm	IEC 60093
Electric strength	813 / -	kV/in	IEC 60243-1
Comparative tracking index	600 / -	-	IEC 60112

Other text information

Injection Molding Preprocessing

XS compounds, stored in a moisture-proof packaging, can be processed without drying; however, it is always recommended drying the product that comes from a large package (e.g. Octabin). The suggested moisture content for the process of injection molding is less than 0.15% for grades with low percentage of reinforcement; for grades with high percentage of fiber and to achieve the best surface quality, the moisture content should be lower than 0.10% . Flame retardant grades must be processed with a maximum moisture content of 0,10%. The drying time depends on the initial moisture content and the drying conditions. Typically 4-8 hours at 80-90C using dehumidified air (dew point of -20C) are suitable conditions for a starting moisture content of 0.20%-0.40%.

Injection molding

The following conditions apply to a standard injection moulding process of XS compounds. Machine temperatures: barrel 265-290C, nozzle and hot runners up to 300C (up to 290C products with flame retardants). Mould temperatures: 80-100C, (80-120C highly reinforced grades). Back pressure: typically 5-10 bar (hydraulic pressure). Temperatures exceeding 300C and long residence time could lead to degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending