

CELANYL® B2 H GF62 NC 1102/3

CELANYL®

Technical grade, designed for the highest stiffness and overall maximum mechanical resistance. Suitable for metal replacement.

Product information

Resin Identification	PA6-GF62	ISO 1043
Part Marking Code	>PA6-GF62<	ISO 11469

Rheological properties

Moulding shrinkage range, parallel	0.1 - 0.3 %	ISO 294-4, 2577
Moulding shrinkage range, normal	0.3 - 0.5 %	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile modulus	20000 / 16000	MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	210 / 145	MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	2 / 3.5	%	ISO 527-1/-2
Flexural modulus	20500 / -	MPa	ISO 178
Flexural strength	360 / -	MPa	ISO 178
Charpy impact strength, 23 °C	80 / 80	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23 °C	18 / -	kJ/m ²	ISO 179/1eA
Izod notched impact strength, 23 °C	18 / 20	kJ/m ²	ISO 180/1A
Poisson's ratio	0.33 / 0.33 ^[C]		

[C]: Calculated

Thermal properties

	dry/cond.		
Melting temperature, 10 °C/min	225 / *	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	213 / *	°C	ISO 75-1/-2

Flammability

	dry/cond.		
Burning Behav. at 1.5mm nom. thickn.	HB / *	class	IEC 60695-11-10

Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	1 / *	%	Sim. to ISO 62
Water absorption, 2mm	3.3 / *	%	Sim. to ISO 62
Density	1730 / -	kg/m ³	ISO 1183

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.15 %
Melt Temperature Optimum	260 °C
Min. melt temperature	240 °C
Max. melt temperature	290 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	80 °C
Min. mould temperature	60 °C

CELANYL® B2 H GF62 NC 1102/3

CELANYL®

Max. mould temperature

120 °C

Characteristics

Processing

Injection Moulding

Delivery form

Granules

Special characteristics

Heat stabilised or stable to heat