

CELANYL® B2 HH J7 GF30 NC 1102/3

CELANYL®

Designed for technical applications that require high mechanical performances, improved toughness and heat ageing resistance.

Product information

Resin Identification	PA6-I-GF30	ISO 1043
Part Marking Code	>PA6-I-GF30<	ISO 11469
Continuous Service Temperature	120 °C	IEC 60216-1

Rheological properties

Moulding shrinkage range, parallel	0.3 - 0.6 %	ISO 294-4, 2577
Moulding shrinkage range, normal	0.6 - 0.9 %	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile modulus	8500/-	MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	140/-	MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	4.5/-	%	ISO 527-1/-2
Flexural modulus	7000/-	MPa	ISO 178
Flexural strength	300/-	MPa	ISO 178
Charpy impact strength, 23°C	100/-	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	22/-	kJ/m ²	ISO 179/1eA
Izod notched impact strength, 23°C	24/-	kJ/m ²	ISO 180/1A
Poisson's ratio	0.34/- ^[C]		
[C]: Calculated			

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	225/*	°C	ISO 11357-1/-3

Flammability

	dry/cond.		
Burning Behav. at 1.5mm nom. thickn.	HB/*	class	IEC 60695-11-10

Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	1.7/*	%	Sim. to ISO 62
Water absorption, 2mm	5.9/*	%	Sim. to ISO 62
Density	1310/-	kg/m ³	ISO 1183

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.15 %
Melt Temperature Optimum	260 °C
Min. melt temperature	240 °C
Max. melt temperature	290 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	80 °C
Min. mould temperature	50 °C

CELANYL® B2 HH J7 GF30 NC 1102/3

CELANYL®

Max. mould temperature

120 °C

Characteristics

Processing

Injection Moulding

Delivery form

Granules

Special characteristics

High impact or impact modified, Heat stabilised or stable to heat