

CELANYL® B3 GF25 NC 1102

CELANYL®

Car industry, Household appliances, Electrical devices.

Product information

Resin Identification	PA6-GF25	ISO 1043
Part Marking Code	>PA6-GF25<	ISO 11469
Continuous Service Temperature	110 °C	IEC 60216-1

Rheological properties

	dry/cond.		
Viscosity number	145 / *	cm ³ /g	ISO 307, 1628
Moulding shrinkage range, parallel	0.2 - 0.6	%	ISO 294-4, 2577
Moulding shrinkage range, normal	0.5 - 0.9	%	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile modulus	7900 / -	MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	165 / -	MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	4 / -	%	ISO 527-1/-2
Charpy impact strength, 23 °C	N / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23 °C	12 / -	kJ/m ²	ISO 179/1eA
Ball indentation hardness, H 961/30	205 / -	MPa	ISO 2039-1
Poisson's ratio	0.34 / - ^[C]		
[C]: Calculated			

Thermal properties

	dry/cond.		
Melting temperature, 10 °C/min	225 / *	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	210 / *	°C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	220 / *	°C	ISO 75-1/-2

Electrical properties

	dry/cond.		
Volume resistivity	1E13 / -	Ohm.m	IEC 62631-3-1
Comparative tracking index	575 / -		IEC 60112

Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	1.8 / *	%	Sim. to ISO 62
Water absorption, 2mm	7.1 / *	%	Sim. to ISO 62
Density	1300 / -	kg/m ³	ISO 1183

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.15 %
Melt Temperature Optimum	260 °C
Min. melt temperature	240 °C
Max. melt temperature	290 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	80 °C

CELANYL® B3 GF25 NC 1102

CELANYL®

Min. mould temperature
Max. mould temperature

60 °C
120 °C

Characteristics

Processing

Injection Moulding