

CELANYL® B3 H GF35 NC 1102/2

CELANYL®

General purpose grade, suitable for any application requiring high mechanical performances and a medium term heat ageing resistance.

Product information

Resin Identification	PA6-GF35	ISO 1043
Part Marking Code	>PA6-GF35<	ISO 11469
Continuous Service Temperature	120 °C	IEC 60216-1

Rheological properties

	dry/cond.		
Moulding shrinkage, parallel	0.5 / -	%	ISO 294-4, 2577
Moulding shrinkage range, parallel	0.3 - 0.6	%	ISO 294-4, 2577
Moulding shrinkage, normal	0.8 / -	%	ISO 294-4, 2577
Moulding shrinkage range, normal	0.6 - 0.9	%	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile modulus	10500 / -	MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	180 / -	MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	3.5 / -	%	ISO 527-1/-2
Flexural modulus	9800 / -	MPa	ISO 178
Charpy impact strength, 23 °C	90 / -	kJ/m ²	ISO 179/1eU
Izod notched impact strength, 23 °C	17 / -	kJ/m ²	ISO 180/1A
Poisson's ratio	0.34 / - ^[C]		

[C]: Calculated

Thermal properties

	dry/cond.		
Melting temperature, 10 °C/min	225 / *	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	208 / *	°C	ISO 75-1/-2

Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	1.6 / *	%	Sim. to ISO 62
Water absorption, 2mm	5.7 / *	%	Sim. to ISO 62
Density	1410 / -	kg/m ³	ISO 1183

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.15 %
Melt Temperature Optimum	260 °C
Min. melt temperature	240 °C
Max. melt temperature	290 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	80 °C
Min. mould temperature	60 °C
Max. mould temperature	120 °C

CELANYL® B3 H GF35 NC 1102/2

CELANYL®

Characteristics

Processing	Injection Moulding
Delivery form	Granules
Special characteristics	Heat stabilised or stable to heat