

CELANYL® B3 HH GF35 NC 1102/HA

CELANYL®

Designed for technical application in automotive, suitable for any application that require long term heat ageing resistance.

Product information

Resin Identification	PA6-GF35	ISO 1043
Part Marking Code	>PA6-GF35<	ISO 11469
Continuous Service Temperature	130 °C	IEC 60216-1

Rheological properties

	dry/cond.		
Moulding shrinkage, parallel	0.3 / -	%	ISO 294-4, 2577
Moulding shrinkage, normal	0.5 / -	%	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile modulus	10800 / -	MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	185 / -	MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	3.3 / -	%	ISO 527-1/-2
Charpy impact strength, 23 °C	80 / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23 °C	15 / -	kJ/m ²	ISO 179/1eA
Izod notched impact strength, 23 °C	14 / -	kJ/m ²	ISO 180/1A
Poisson's ratio	0.34 / - ^[C]		

[C]: Calculated

Thermal properties

	dry/cond.		
Melting temperature, 10 °C/min	225 / *	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	210 / *	°C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	220 / *	°C	ISO 75-1/-2

Flammability

	dry/cond.		
Burning Behav. at 1.5mm nom. thickn.	HB / *	class	IEC 60695-11-10
Thickness tested	1.6 / *	mm	IEC 60695-11-10
Burning Behav. at thickness h	HB / *	class	IEC 60695-11-10
Thickness tested	0.8 / *	mm	IEC 60695-11-10

Electrical properties

	dry/cond.		
Electric strength	21 / -	kV/mm	IEC 60243-1

Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	1.5 / *	%	Sim. to ISO 62
Water absorption, 2mm	6 / *	%	Sim. to ISO 62
Density	1410 / -	kg/m ³	ISO 1183

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.15 %
Melt Temperature Optimum	260 °C

CELANYL® B3 HH GF35 NC 1102/HA

CELANYL®

Min. melt temperature	240 °C
Max. melt temperature	290 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	80 °C
Min. mould temperature	60 °C
Max. mould temperature	120 °C

Characteristics

Processing	Injection Moulding
Delivery form	Granules
Special characteristics	Heat stabilised or stable to heat