

CELANYL® B3 HH SGF1809 BK 9005/2

CELANYL®

*Designed for Automotive industry, suitable for other technical applications that require high stiffness and low warpage.
Long term heat ageing resistance, good surface quality.*

Product information

Resin Identification	PA6-(GF+MD)3 0	ISO 1043
Part Marking Code	>PA6-(GF+MD)30<	ISO 11469
Continuous Service Temperature	120 °C	IEC 60216-1

Rheological properties

Moulding shrinkage range, parallel	0.4 - 0.6 %	ISO 294-4, 2577
Moulding shrinkage range, normal	0.6 - 0.8 %	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile modulus	8000 / -	MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	105 / -	MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	2.8 / -	%	ISO 527-1/-2
Flexural modulus	7700 / -	MPa	ISO 178
Charpy impact strength, 23 °C	50 / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23 °C	5 / -	kJ/m ²	ISO 179/1eA
Izod notched impact strength, 23 °C	5 / -	kJ/m ²	ISO 180/1A
Poisson's ratio	0.34 / - ^[C]		

[C]: Calculated

Thermal properties

	dry/cond.		
Melting temperature, 10 °C/min	225 / *	°C	ISO 11357-1/-3

Flammability

	dry/cond.		
Burning Behav. at 1.5mm nom. thickn.	HB / *	class	IEC 60695-11-10

Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	1.8 / *	%	Sim. to ISO 62
Water absorption, 2mm	6.3 / *	%	Sim. to ISO 62
Density	1370 / -	kg/m ³	ISO 1183

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.15 %
Melt Temperature Optimum	260 °C
Min. melt temperature	240 °C
Max. melt temperature	290 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	80 °C
Min. mould temperature	60 °C

CELANYL® B3 HH SGF1809 BK 9005/2

CELANYL®

Max. mould temperature

120 °C

Characteristics

Processing

Injection Moulding

Delivery form

Granules

Special characteristics

Heat stabilised or stable to heat, High Flow, Low Warpage