

CELANYL® B3 L NC 1102

CELANYL®

General purpose grade designed for high productivity and good aesthetical results

Product information

Resin Identification	PA6	ISO 1043
Part Marking Code	>PA6<	ISO 11469
Continuous Service Temperature	95 °C	IEC 60216-1

Rheological properties

	dry/cond.		
Viscosity number	145/*	cm ³ /g	ISO 307, 1628
Moulding shrinkage range, parallel	1.4 - 1.8	%	ISO 294-4, 2577
Moulding shrinkage range, normal	1.4 - 1.8	%	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile modulus	3250/-	MPa	ISO 527-1/-2
Tensile stress at yield, 50mm/min	85/-	MPa	ISO 527-1/-2
Tensile strain at break, 50mm/min	5/-	%	ISO 527-1/-2
Charpy impact strength, 23°C	N/-	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	3.5/-	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	3/-	kJ/m ²	ISO 179/1eA
Ball indentation hardness, H 961/30	155/-	MPa	ISO 2039-1
Poisson's ratio	0.37/- ^[C]		

[C]: Calculated

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	225/*	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	70/*	°C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	180/*	°C	ISO 75-1/-2

Electrical properties

	dry/cond.		
Volume resistivity	1E13/-	Ohm.m	IEC 62631-3-1
Electric strength	20/-	kV/mm	IEC 60243-1
Comparative tracking index	600/-		IEC 60112

Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	2/*	%	Sim. to ISO 62
Water absorption, 2mm	8.5/*	%	Sim. to ISO 62
Density	1120/-	kg/m ³	ISO 1183

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.15 %
Melt Temperature Optimum	260 °C
Min. melt temperature	235 °C
Max. melt temperature	270 °C

CELANYL® B3 L NC 1102

CELANYL®

Screw tangential speed	≤0.3 m/s
Mold Temperature Optimum	70 °C
Min. mould temperature	50 °C
Max. mould temperature	100 °C

Characteristics

Processing	Injection Moulding
Additives	Nucleated
Special characteristics	Low wear / Low friction, High Flow