

CELANYL® B3 W MGF2015 NC 1102/1

CELANYL®

Product information

Resin Identification	PA6-(GF+MD)3 5	ISO 1043
Part Marking Code	>PA6-(GF+MD)35<	ISO 11469

Typical mechanical properties

Izod notched impact strength, 23 °C	dry/cond. 3.7 / -	kJ/m ²	ISO 180/1A
-------------------------------------	----------------------	-------------------	------------

Physical/Other properties

Density	dry/cond. 1380 / -	kg/m ³	ISO 1183
---------	-----------------------	-------------------	----------

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.15 %
Melt Temperature Optimum	260 °C
Min. melt temperature	240 °C
Max. melt temperature	290 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	80 °C
Min. mould temperature	60 °C
Max. mould temperature	120 °C

Characteristics

Processing	Injection Moulding
Special characteristics	Heat stabilised or stable to heat, Low Warpage