

## ECOMID® B HH GF15 BK 9005/1P - PA6

### Description

Polyamide 6 compound, 15% glass fiber reinforced, heat stabilized.

*Designed for Automotive parts requiring high thermal ageing resistance. Based on recycled polyamide.*

Preliminary Technical Datasheet


Physical properties	Value	Unit	Test Standard
Density	77.4	lb/ft <sup>3</sup>	ISO 1183
Molding shrinkage, parallel (flow)	0.4 - 0.8	%	ISO 294-4, 2577
Molding shrinkage, transverse normal	0.8 - 1.2	%	ISO 294-4, 2577
Water absorption, 23°C-sat	7.8	%	Sim. to ISO 62
Humidity absorption, 23°C/50%RH	2.3	%	ISO 62
Viscosity number (PA), H <sub>2</sub> SO <sub>4</sub>	140	ml/g	ISO 307 (PA)

Mechanical properties	Value	Unit	Test Standard
Tensile modulus	870228/435114	psi	ISO 527-1, -2
Tensile stress at break, 5mm/min	16000/8700	psi	ISO 527-1, -2
Tensile strain at break, 5mm/min	3.5/>10	%	ISO 527-1, -2
Flexural modulus, 23°C	812000/-	psi	ISO 178
Flexural strength, 23°C	23900/-	psi	ISO 178
Charpy impact strength, 23°C	19/>100	ft-lb/in <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	14.3/19	ft-lb/in <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23°C	1.66/4.28	ft-lb/in <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	1.43/1.43	ft-lb/in <sup>2</sup>	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
Melting temperature, 20°C/min	428	°F	ISO 11357-1/-3
DTUL at 1.8 MPa	365	°F	ISO 75-1, -2
DTUL at 0.45 MPa	419	°F	ISO 75-1, -2
Vicat softening temperature, 50°C/h 50N	401	°F	ISO 306
Flammability @3.2mm nom. thickn.	HB	class	UL 94
Continuous service temperature	130	°C	DIN/IEC 60216-1


Diagrams

Stress-strain (dry)




Dry sample dry as molded  
Conditioned sample conditioned according to ISO 1110

Stress-strain (cond.)






Dry sample dry as molded  
Conditioned sample conditioned according to ISO 1110

Secant modulus-strain (dry)



Secant modulus-strain (cond.)





**Other text information**

**Injection Molding Preprocessing**

PA materials, stocked in a moisture-proof packaging, can be processed without drying; however, it is always recommended drying the product that comes from a large package (e.g. Octabin). The moisture content suggested for the injection molding process should be lower than 0.15%, according to the grade and to the molded part characteristics. The materials containing flame retardants should have moisture content below 0.10%. Red phosphorous containing grades must always be dried below 0.08%. The drying time depends on the moisture content and the drying conditions. Typically, 4-8 hours at 80-90 °C using dehumidified air (dew point of -20 °C) are suitable conditions for a starting moisture content of 0.20%-0.40%.

**Injection molding**

The following conditions apply to a standard injection molding process. Machine temperatures: barrel 265-290 °C (PA66), 235-270 °C (PA6), nozzle and hot runners up to 300 °C (up to 290 °C products with flame retardants). Mold temperatures: 60-80 °C, (80-100 °C highly reinforced grades). Back pressure: typically, 5-10 bar (hydraulic pressure). Temperatures exceeding 300 °C and long residence time could lead to additives degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending on the molded part characteristics. For further details, please refer to the document 'Instructions for injection molding' or contact our technical support team.

**Injection Molding Postprocessing**

PA materials reach their final performance with a water content of about 1.5 to 3.5% by weight, depending on the type. This percentage corresponds to the point of equilibrium between the rates of absorption and desorption of moisture. After molding, in favorable environmental conditions, a part can quickly absorb moisture up to 0.5-1.0%, while the equilibrium will be reached during its life. A conditioning treatment can accelerate further the initial water absorption of the molded parts. Conditioning is usually carried out in hot and humid environment (for example 50 °C, 100% RH), inside climatic chambers. Slight dimensional variations (increase in volume due to the water absorbed) must be considered, especially in unfilled grades. Post-treatments of parts may also include the annealing (60-80 °C in oven, up to four hours). This procedure can be useful to relax any internal stresses.

**Characteristics**

<b>Special Characteristics</b>	Heat resistant, Recycled content
<b>Product Categories</b>	Glass reinforced
<b>Processing</b>	Injection molding

(+) 18816996168

ECOMID® B HH GF15 BK 9005/1P - PA6

Ponciplastics.com

Delivery Form

Granules

**Other Approvals**

OEM	Specification	Additional Information
VW Group*	VW50134	* best fitting grade to PA6-3-A, not officially approved
VW Group*	VW50125	* best fitting grade to PA6-4, not officially approved