

FRIANYL® B S25 V2 ECO-R NC 1102 (PRELIMINARY)

Polyamide 6 compound, 25% mineral reinforced, flame retardant, halogen and red phosphorous free. Classified V2@0.75mm. Partially based on recyclate polymer.

Designed for Electrical applications requiring self-extinguishing properties combined with low warpage, good flowability and surface quality.

Product information

Part Marking Code	>PA6-MD25 FR(30)<	ISO 11469
-------------------	-------------------	-----------

Rheological properties

Viscosity number	135 cm ³ /g	ISO 307, 1157, 1628
Moulding shrinkage range, parallel	0.6 - 1.0 %	ISO 294-4, 2577
Moulding shrinkage range, normal	0.6 - 1.0 %	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.	
Tensile Modulus	6400/- MPa	ISO 527-1/-2
Stress at break, 5mm/min	62/- MPa	ISO 527-1/-2
Strain at break, 5mm/min	1.8/- %	ISO 527-1/-2
Charpy impact strength, 23°C	20/- kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	20/- kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	1.8/- kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	1.7/- kJ/m ²	ISO 179/1eA

Thermal properties

Melting temperature, 10°C/min	225 °C	ISO 11357-1/-3
Vicat softening temperature, 50°C/h 10N	214 °C	ISO 306

Flammability

Burning Behav. at thickness h	V-2 class	UL 94
Glow Wire Flammability Index, 0.75mm	960 °C	IEC 60695-2-12
Glow Wire Flammability Index, 3mm	960 °C	IEC 60695-2-12
FMVSS Class	SE	ISO 3795 (FMVSS 302)

Electrical properties

Comparative tracking index	Group I	IEC 60112
----------------------------	---------	-----------

Other properties

Humidity absorption, 2mm	1.7 %	Sim. to ISO 62
Water absorption, 2mm	6.7 %	Sim. to ISO 62
Density	1350 kg/m ³	ISO 1183

FRIANYL® B S25 V2 ECO-R NC 1102 (PRELIMINARY)

Characteristics

Additives

Flame retardant, Mineral Filler, Non-halogenated/Red phosphorous free flame retardant, Contains Recycle

Additional information

Injection molding

The following conditions apply to a standard injection molding process. Machine temperatures: barrel 265-290°C (PA66), 235-270°C (PA6), nozzle and hot runners up to 300°C (up to 290°C products with flame retardants). Mold temperatures: 60-80°C, (80-100°C highly reinforced grades). Back pressure: typically, 5-10 bar (hydraulic pressure). Temperatures exceeding 300°C and long residence time could lead to additives degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending on the molded part characteristics. For further details, please refer to the document 'Instructions for injection molding' or contact our technical support team.

Processing Texts

Injection molding

The following conditions apply to a standard injection molding process. Machine temperatures: barrel 265-290°C (PA66), 235-270°C (PA6), nozzle and hot runners up to 300°C (up to 290°C products with flame retardants). Mold temperatures: 60-80°C, (80-100°C highly reinforced grades). Back pressure: typically, 5-10 bar (hydraulic pressure). Temperatures exceeding 300°C and long residence time could lead to additives degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending on the molded part characteristics. For further details, please refer to the document 'Instructions for injection molding' or contact our technical support team.

Injection molding Preprocessing

PA materials, stocked in a moisture-proof packaging, can be processed without drying; however, it is always recommended drying the product that comes from a large package (e.g. Octabin). The moisture content suggested for the injection molding process should be lower than 0.15%, according to the grade and to the molded part characteristics. The materials containing flame retardants should have moisture content below 0.10%. Red phosphorous containing grades must always be dried below 0.08%. The drying time depends on the moisture content and the drying conditions. Typically, 4-8 hours at 80-90°C using dehumidified air (dew point of -20°C) are suitable conditions for a starting moisture content of 0.20%-0.40%.

Injection molding Postprocessing

PA materials reach their final performance with a water content of about 1.5 to 3.5% by weight, depending on the type. This percentage corresponds to the point of equilibrium between the rates of absorption and desorption of moisture. After molding, in favorable environmental conditions, a part can quickly absorb moisture up to 0.5-1.0%, while the equilibrium will be reached during its life. A

FRIANYL® B S25 V2 ECO-R NC 1102 (PRELIMINARY)

conditioning treatment can accelerate further the initial water absorption of the molded parts. Conditioning is usually carried out in hot and humid environment (for example 50°C, 100% RH), inside climatic chambers. Slight dimensional variations (increase in volume due to the water absorbed) must be considered, especially in unfilled grades. Post-treatments of parts may also include the annealing (60-80°C in oven, up to four hours). This procedure can be useful to relax any internal stresses.