

# FRIANYL® B3 H V0 BK 9011/TB

Polyamide 6 compound, unfilled, heat resistant, based on flame retardants halogen and red phosphorous free. UL listed V0@0,8mm

*Designed for any electrical application that require self-extinguishing properties, excellent surface quality and flexibility of use.*

## Product information

Part Marking Code	PA6 FR(30)	ISO 11469
-------------------	------------	-----------

## Rheological properties

Moulding shrinkage range, parallel	1.1 - 1.5 %	ISO 294-4, 2577
Moulding shrinkage range, normal	1.1 - 1.5 %	ISO 294-4, 2577

## Typical mechanical properties

	dry/cond.		
Tensile Modulus	3300/-	MPa	ISO 527-1/-2
Yield stress, 50mm/min	70/-	MPa	ISO 527-1/-2
Yield strain, 50mm/min	3.2/-	%	ISO 527-1/-2
Flexural Modulus	3000/-	MPa	ISO 178
Flexural Strength	125/-	MPa	ISO 178
Charpy impact strength, 23°C	40/-	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23°C	3/-	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, 23°C	3.5/-	kJ/m <sup>2</sup>	ISO 180/1A

## Thermal properties

Melting temperature, 10°C/min	225 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	70 °C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	190 °C	ISO 75-1/-2
RTI, electrical, 0.75mm	130 °C	UL 746B
RTI, impact, 0.75mm	95 °C	UL 746B
RTI, strength, 0.75mm	130 °C	UL 746B

## Flammability

Burning Behav. at 1.5mm nom. thickn.	V-0 class	UL 94
Thickness tested	1.6 mm	UL 94
Burning Behav. at thickness h	V-0 class	UL 94
Thickness tested	3.2 mm	UL 94
Glow Wire Flammability Index, 0.75mm	960 °C	IEC 60695-2-12
Glow Wire Flammability Index, 3mm	960 °C	IEC 60695-2-12

# FRIANYL® B3 H V0 BK 9011/TB

## Other properties

Humidity absorption, 2mm	2 %	Sim. to ISO 62
Water absorption, 2mm	9 %	Sim. to ISO 62
Density	1170 kg/m <sup>3</sup>	ISO 1183

## Characteristics

Additives	Flame retardant, Non-halogenated/Red phosphorous free flame retardant
-----------	---

## Additional information

Injection molding	The following conditions apply to a standard injection moulding process. Machine temperatures: barrel 265-290C (PA66), 235-270C (PA6), nozzle and hot runners up to 300C (up to 290C products with flame retardants). Mould temperatures: 60-80C, (80-100C highly reinforced grades). Back pressure: typically 5-10 bar (hydraulic pressure). Temperatures exceeding 300C and long residence time could lead to additives degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending on the moulded part characteristics. For further details, please refer to the document 'Instructions for injection moulding' or contact our technical support team.
-------------------	--

## Processing Texts

Injection molding	The following conditions apply to a standard injection moulding process. Machine temperatures: barrel 265-290C (PA66), 235-270C (PA6), nozzle and hot runners up to 300C (up to 290C products with flame retardants). Mould temperatures: 60-80C, (80-100C highly reinforced grades). Back pressure: typically 5-10 bar (hydraulic pressure). Temperatures exceeding 300C and long residence time could lead to additives degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending on the moulded part characteristics. For further details, please refer to the document 'Instructions for injection moulding' or contact our technical support team.
Injection molding Preprocessing	PA materials, stocked in a moisture-proof packaging, can be processed without drying; however, it is always recommended drying the product that comes from a large package (e.g. Octabin). The moisture content suggested for the injection moulding process should be lower than 0.15%, according to the grade and to the moulded part characteristics. The materials containing flame retardants should have moisture content below 0.10%. Red phosphorous containing grades must always be dried below 0.08%. The drying time depends on the moisture content and the drying conditions. Typically 4-8 hours at 80-90C using dehumidified air (dew point of -20C) are suitable conditions for a starting moisture content of 0.20%-0.40%.
Injection molding Postprocessing	PA materials reach their final performance with a water content of about 1.5 to

# FRIANYL® B3 H V0 BK 9011/TB

3.5% by weight, depending on the type. This percentage corresponds to the point of equilibrium between the rates of absorption and desorption of moisture. After moulding, in favourable environmental conditions, a part can quickly absorb moisture up to 0.5-1.0%, while the equilibrium will be reached during its life. A conditioning treatment can accelerate further the initial water absorption of the moulded parts. Conditioning is usually carried out in hot and humid environment (for example 50C, 100% RH), inside climatic chambers. Slight dimensional variations (increase in volume due to the water absorbed) must be taken into account, especially in unfilled grades. Post-treatments of parts may also include the annealing (60-80C in oven, up to four hours). This procedure can be useful to relax any internal stresses.

---