

## FRIANYL B3 V2 NC 1102 - PA6

### Description

Car industry, Household appliances, Electrical devices.

Physical properties	dry / cond	Unit	Test Standard
Density	70.5 / -	lb/ft <sup>3</sup>	ISO 1183
Molding shrinkage, parallel	1.6 - 2.0	%	ISO 294-4, 2577
Molding shrinkage, normal	1.6 - 2.0	%	ISO 294-4, 2577
Water absorption, 23°C-sat	9 / *	%	ISO 62
Humidity absorption, 23°C/50%RH	2.5 / *	%	ISO 62
Viscosity number (PA), H2SO4	145 / *	-	ISO 307 (PA)

Mechanical properties	dry / cond	Unit	Test Standard
Tensile modulus	449618 / -	psi	ISO 527-2/1A
Tensile stress at yield, 50mm/min	11600 / -	psi	ISO 527-2/1A
Tensile strain at yield, 50mm/min	4.5 / -	%	ISO 527-2/1A
Tensile strain at break, 50mm/min	10 / -	%	ISO 527-2/1A
Charpy impact strength, 23°C	NB / -	ft-lb/in <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	NB / -	ft-lb/in <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23°C	1.9 / -	ft-lb/in <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	1.66 / -	ft-lb/in <sup>2</sup>	ISO 179/1eA
Ball indentation hardness, 30s	22500	psi	ISO 2039-1

Thermal properties	dry / cond	Unit	Test Standard
Melting point, peak	428	°F	ISO 3146
DTUL at 1.8 MPa	149 / *	°F	ISO 75-1, -2
DTUL at 0.45 MPa	338 / *	°F	ISO 75-1, -2
Flammability @3.2mm nom. thickn.	V-2 / *	class	UL 94
Flammability @0.8mm nom. thickn.	V-2 / *	class	UL 94
Flammability @0.4mm nom. thickn.	V-2 / *	class	UL 94
Continuous service temperature	125 / *	°C	DIN/IEC 60216-1

Electrical properties	dry / cond	Unit	Test Standard
Volume resistivity	1E15 / -	Ohm*m	IEC 60093
Comparative tracking index	PLC 0 / -	-	IEC 60112

### Other text information

#### Injection Molding Preprocessing

PA materials, stocked in a moisture-proof packaging, can be processed without drying; however, it is always recommended drying the product that comes from a large package (e.g. Octabin). The moisture content suggested for the injection moulding process should be lower than 0.15%, according to the grade and to the moulded part characteristics. The materials containing flame retardants should have moisture content below 0.10%. Red phosphorous containing grades must always be dried below 0.08%. The drying time depends on the moisture content and the drying conditions. Typically 4-8 hours at 80-90°C using dehumidified air (dew point of -20°C) are suitable conditions for a starting moisture content of 0.20%-0.40%.

#### Injection molding

The following conditions apply to a standard injection moulding process. Machine temperatures: barrel 265-290°C (PA66), 235-270°C (PA6), nozzle and hot runners up to 300°C (up to 290°C products with flame retardants). Mould temperatures: 60-80°C, (80-100°C highly reinforced grades). Back pressure: typically 5-10 bar (hydraulic pressure). Temperatures exceeding 300°C and long residence time could lead to additives degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending on the moulded part characteristics. For further details, please refer to the document "Instructions for injection moulding" or contact our technical support team.