

CELANYL® A3 GF35 BK 9005/U

CELANYL®

Car industry, Household appliances, Electrical devices.

Product information

Resin Identification	PA66-GF35	ISO 1043
Part Marking Code	>PA66-GF35<	ISO 11469
Continuous Service Temperature	90 °C	IEC 60216-1

Rheological properties

	dry/cond.		
Viscosity number	140 / *	cm ³ /g	ISO 307, 1628
Moulding shrinkage range, parallel	0.3 - 0.6	%	ISO 294-4, 2577
Moulding shrinkage range, normal	0.8 - 1.3	%	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile modulus	10500 / -	MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	175 / -	MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	2.6 / -	%	ISO 527-1/-2
Charpy impact strength, 23 °C	50 / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23 °C	8.5 / -	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30 °C	7 / -	kJ/m ²	ISO 179/1eA
Ball indentation hardness, H 961/30	180 / -	MPa	ISO 2039-1
Poisson's ratio	0.34 / - ^[C]		

[C]: Calculated

Thermal properties

	dry/cond.		
Melting temperature, 10 °C/min	265 / *	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	240 / *	°C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	250 / *	°C	ISO 75-1/-2

Electrical properties

	dry/cond.		
Volume resistivity	1E13 / -	Ohm.m	IEC 62631-3-1
Comparative tracking index	550 / -		IEC 60112

Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	1.4 / *	%	Sim. to ISO 62
Water absorption, 2mm	5.2 / *	%	Sim. to ISO 62
Density	1400 / -	kg/m ³	ISO 1183

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.15 %
Melt Temperature Optimum	295 °C
Min. melt temperature	285 °C
Max. melt temperature	305 °C
Screw tangential speed	≤0.2 m/s

CELANYL® A3 GF35 BK 9005/U

CELANYL®

Mold Temperature Optimum	100 °C
Min. mould temperature	70 °C
Max. mould temperature	120 °C

Characteristics

Processing	Injection Moulding
Delivery form	Granules
Special characteristics	High Flow