

# CELANYL® A3 HH GF30 NC 1102/HA

Polyamide 66 compound, 30% glass fibre reinforced, heat stabilized. UL certified HB@0.75mm.

*Designed for technical application in automotive, suitable for any application that require long term heat ageing resistance.*

## Product information

Part Marking Code

>PA66-GF30<

ISO 11469

## Rheological properties

Moulding shrinkage range, parallel

0.3 - 0.6 %

ISO 294-4, 2577

Moulding shrinkage range, normal

0.6 - 0.9 %

ISO 294-4, 2577

## Typical mechanical properties

dry/cond.

Tensile Modulus

10000/-

MPa

ISO 527-1/-2

Stress at break, 5mm/min

185/-

MPa

ISO 527-1/-2

Strain at break, 5mm/min

2.5/-

%

ISO 527-1/-2

Flexural Modulus

9600/-

MPa

ISO 178

Charpy impact strength, 23°C

70/-

kJ/m<sup>2</sup>

ISO 179/1eU

Charpy impact strength, -30°C

>50/-

kJ/m<sup>2</sup>

ISO 179/1eU

Charpy notched impact strength, 23°C

10.5/-

kJ/m<sup>2</sup>

ISO 179/1eA

Charpy notched impact strength, -30°C

9/-

kJ/m<sup>2</sup>

ISO 179/1eA

Izod notched impact strength, 23°C

11/-

kJ/m<sup>2</sup>

ISO 180/1A

Izod notched impact strength, -30°C

10

kJ/m<sup>2</sup>

ISO 180/1A

Izod impact strength, 23°C

60/-

kJ/m<sup>2</sup>

ISO 180/1U

## Thermal properties

Melting temperature, 10°C/min

265 °C

ISO 11357-1/-3

Temp. of deflection under load, 1.8 MPa

250 °C

ISO 75-1/-2

Temp. of deflection under load, 0.45 MPa

260 °C

ISO 75-1/-2

## Flammability

Burning Behav. at thickness h

HB class

UL 94

FMVSS Class

B

ISO 3795 (FMVSS 302)

## Electrical properties

dry/cond.

Volume resistivity

>1E13/-

Ohm.m

IEC 62631-3-1

Surface resistivity

>1E13/-

Ohm

IEC 62631-3-2

Comparative tracking index

Group I

IEC 60112

Comparative tracking index

PLC 0/-

PLC

UL 746A

# CELANYL® A3 HH GF30 NC 1102/HA

## Other properties

Humidity absorption, 2mm	1.7 %	Sim. to ISO 62
Water absorption, 2mm	5.9 %	Sim. to ISO 62
Density	1370 kg/m <sup>3</sup>	ISO 1183

## Additional information

Injection molding	The following conditions apply to a standard injection molding process. Machine temperatures: barrel 265-290°C (PA66), 235-270°C (PA6), nozzle and hot runners up to 300°C (up to 290°C products with flame retardants). Mold temperatures: 60-80°C, (80-100°C highly reinforced grades). Back pressure: typically, 5-10 bar (hydraulic pressure). Temperatures exceeding 300°C and long residence time could lead to additives degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending on the molded part characteristics. For further details, please refer to the document 'Instructions for injection molding' or contact our technical support team.
-------------------	--

## Processing Texts

Injection molding	The following conditions apply to a standard injection molding process. Machine temperatures: barrel 265-290°C (PA66), 235-270°C (PA6), nozzle and hot runners up to 300°C (up to 290°C products with flame retardants). Mold temperatures: 60-80°C, (80-100°C highly reinforced grades). Back pressure: typically, 5-10 bar (hydraulic pressure). Temperatures exceeding 300°C and long residence time could lead to additives degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending on the molded part characteristics. For further details, please refer to the document 'Instructions for injection molding' or contact our technical support team.
Injection molding Preprocessing	PA materials, stocked in a moisture-proof packaging, can be processed without drying; however, it is always recommended drying the product that comes from a large package (e.g. Octabin). The moisture content suggested for the injection molding process should be lower than 0.15%, according to the grade and to the molded part characteristics. The materials containing flame retardants should have moisture content below 0.10%. Red phosphorous containing grades must always be dried below 0.08%. The drying time depends on the moisture content and the drying conditions. Typically, 4-8 hours at 80-90°C using dehumidified air (dew point of -20°C) are suitable conditions for a starting moisture content of 0.20%-0.40%.
Injection molding Postprocessing	PA materials reach their final performance with a water content of about 1.5 to 3.5% by weight, depending on the type. This percentage corresponds to the point of equilibrium between the rates of absorption and desorption of moisture. After molding, in favorable environmental conditions, a part can quickly absorb moisture up to 0.5-1.0%, while the equilibrium will be reached during its life. A

# CELANYL® A3 HH GF30 NC 1102/HA

conditioning treatment can accelerate further the initial water absorption of the molded parts. Conditioning is usually carried out in hot and humid environment (for example 50°C, 100% RH), inside climatic chambers. Slight dimensional variations (increase in volume due to the water absorbed) must be considered, especially in unfilled grades. Post-treatments of parts may also include the annealing (60-80°C in oven, up to four hours). This procedure can be useful to relax any internal stresses.