

CELANYL® A3 J20 NC 1102/E

CELANYL®

Car industry, Household appliances, Electrical devices.

Product information

Resin Identification	PA66-I	ISO 1043
Part Marking Code	>PA66-I<	ISO 11469
Continuous Service Temperature	85 °C	IEC 60216-1

Rheological properties

Moulding shrinkage range, parallel	1.2 - 1.6 %	ISO 294-4, 2577
Moulding shrinkage range, normal	1.2 - 1.6 %	ISO 294-4, 2577

Typical mechanical properties

	dry/cond.		
Tensile modulus	1800 / -	MPa	ISO 527-1/-2
Tensile stress at yield, 50mm/min	49 / -	MPa	ISO 527-1/-2
Tensile strain at yield, 50mm/min	10 / -	%	ISO 527-1/-2
Flexural modulus	1700 / -	MPa	ISO 178
Flexural strength	65 / -	MPa	ISO 178
Charpy impact strength, 23 °C	N / -	kJ/m ²	ISO 179/1eU
Izod notched impact strength, 23 °C	75 / -	kJ/m ²	ISO 180/1A
Izod notched impact strength, -30 °C	20.0 / -	kJ/m ²	ISO 180/1A
Poisson's ratio	0.41 / - ^[C]		

[C]: Calculated

Thermal properties

	dry/cond.		
Melting temperature, 10 °C/min	260 / *	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	60 / *	°C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	160 / *	°C	ISO 75-1/-2

Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	1.7 / *	%	Sim. to ISO 62
Water absorption, 2mm	6.8 / *	%	Sim. to ISO 62
Density	1060 / -	kg/m ³	ISO 1183

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.15 %
Melt Temperature Optimum	290 °C
Min. melt temperature	280 °C
Max. melt temperature	300 °C
Screw tangential speed	≤0.3 m/s
Mold Temperature Optimum	80 °C
Min. mould temperature	50 °C
Max. mould temperature	100 °C

CELANYL® A3 J20 NC 1102/E

CELANYL®

Characteristics

Processing	Injection Moulding
Special characteristics	High impact or impact modified