

# CELANYL® A3 W GF30 BK 9005/Y

Polyamide 66 compound, 30% glass fiber reinforced, heat stabilized. UL certified HB@1.5mm.

*General purpose grade, suitable for many technical applications. Medium term heat ageing resistance. Improved flowability.*

## Product information

Part Marking Code	>(PA66+PA6)-GF30<	ISO 11469
-------------------	-------------------	-----------

## Rheological properties

Viscosity number	145 cm <sup>3</sup> /g	ISO 307, 1157, 1628
Moulding shrinkage range, parallel	0.3 - 0.6 %	ISO 294-4, 2577
Moulding shrinkage range, normal	0.6 - 0.9 %	ISO 294-4, 2577

## Typical mechanical properties

	dry/cond.		
Tensile Modulus	9250 / 5400	MPa	ISO 527-1/-2
Stress at break, 5mm/min	150 / 90	MPa	ISO 527-1/-2
Strain at break, 5mm/min	3 / 9	%	ISO 527-1/-2
Flexural Modulus	9500 / -	MPa	ISO 178
Flexural Strength	270 / -	MPa	ISO 178
Charpy impact strength, 23°C	N / -	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	N / -	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23°C	7.5 / 11	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	6.5 / -	kJ/m <sup>2</sup>	ISO 179/1eA
Ball indentation hardness, H 358/30	200	MPa	ISO 2039-1

## Thermal properties

Melting temperature, 10°C/min	260 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	240 °C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	250 °C	ISO 75-1/-2

## Flammability

Burning Behav. at 1.5mm nom. thickn.	HB class	UL 94
Burning Behav. at thickness h	HB class	UL 94
FMVSS Class	B	ISO 3795 (FMVSS 302)

## Electrical properties

	dry/cond.		
Volume resistivity	1E13 / -	Ohm.m	IEC 62631-3-1

## Other properties

Humidity absorption, 2mm	1.7 %	Sim. to ISO 62
Water absorption, 2mm	6 %	Sim. to ISO 62
Density	1360 kg/m <sup>3</sup>	ISO 1183

# CELANYL® A3 W GF30 BK 9005/Y

## VDA Properties

Emission of organic compounds	10.2 µgC/g	VDA 277
Odour	4.2 class	VDA 270

## Injection

Melt Temperature Optimum	278 °C	Internal
--------------------------	--------	----------

## Additional information

Injection molding	<p>The following conditions apply to a standard injection molding process. Machine temperatures: barrel 265-290°C (PA66), 235-270°C (PA6), nozzle and hot runners up to 300°C (up to 290°C products with flame retardants). Mold temperatures: 60-80°C, (80-100°C highly reinforced grades). Back pressure: typically, 5-10 bar (hydraulic pressure). Temperatures exceeding 300°C and long residence time could lead to additives degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending on the molded part characteristics. For further details, please refer to the document 'Instructions for injection molding' or contact our technical support team.</p>	
-------------------	---	--

## Processing Texts

Injection molding	<p>The following conditions apply to a standard injection molding process. Machine temperatures: barrel 265-290°C (PA66), 235-270°C (PA6), nozzle and hot runners up to 300°C (up to 290°C products with flame retardants). Mold temperatures: 60-80°C, (80-100°C highly reinforced grades). Back pressure: typically, 5-10 bar (hydraulic pressure). Temperatures exceeding 300°C and long residence time could lead to additives degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending on the molded part characteristics. For further details, please refer to the document 'Instructions for injection molding' or contact our technical support team.</p>	
Injection molding Preprocessing	<p>PA materials, stocked in a moisture-proof packaging, can be processed without drying; however, it is always recommended drying the product that comes from a large package (e.g. Octabin). The moisture content suggested for the injection molding process should be lower than 0.15%, according to the grade and to the molded part characteristics. The materials containing flame retardants should have moisture content below 0.10%. Red phosphorous containing grades must always be dried below 0.08%. The drying time depends on the moisture content and the drying conditions. Typically, 4-8 hours at 80-90°C using dehumidified air (dew point of -20°C) are suitable conditions for a starting moisture content of 0.20%-0.40%.</p>	
Injection molding Postprocessing	<p>PA materials reach their final performance with a water content of about 1.5 to 3.5% by weight, depending on the type. This percentage corresponds to the point of equilibrium between the rates of absorption and desorption of moisture. After</p>	

# CELANYL® A3 W GF30 BK 9005/Y

molding, in favorable environmental conditions, a part can quickly absorb moisture up to 0.5-1.0%, while the equilibrium will be reached during its life. A conditioning treatment can accelerate further the initial water absorption of the molded parts. Conditioning is usually carried out in hot and humid environment (for example 50°C, 100% RH), inside climatic chambers. Slight dimensional variations (increase in volume due to the water absorbed) must be considered, especially in unfilled grades. Post-treatments of parts may also include the annealing (60-80°C in oven, up to four hours). This procedure can be useful to relax any internal stresses.

## Other Approvals

### Other Approvals

OEM	Specification	Additional Information
Mercedes-Benz Group (Daimler)	DBL 5408	
VW Group*	VW50133	* best fitting grade, not officially approved
SAIC Motor	SMTC 5 310 015	