

CELSTRAN® PA66-CF40-02 AF3004 NATURAL

CELSTRAN® Long Fibre

Celstran® PA66-CF40-02 is a 40% long **carbon fiber** 66 polyamid. This material imparts excellent impact and extremely high modulus properties that exceed that of short carbon fiber PA66. High heat distortion temperatures and good chemical resistance makes Celstran PA66 the perfect product for metal replacement applications

Product information

Resin Identification	PA66-LCF40	ISO 1043
Part Marking Code	>PA66-LCF40<	ISO 11469

Typical mechanical properties

Tensile modulus	30900 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	294 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	1 %	ISO 527-1/-2
Flexural modulus	26000 MPa	ISO 178
Flexural strength	460 MPa	ISO 178
Charpy notched impact strength, 23°C	23 kJ/m ²	ISO 179/1eA
Poisson's ratio	0.33 ^[C]	

[C]: Calculated

Thermal properties

Temperature of deflection under load, 1.8 MPa	260 °C	ISO 75-1/-2
---	--------	-------------

Physical/Other properties

Density	1340 kg/m ³	ISO 1183
---------	------------------------	----------

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.2 %
Melt Temperature Optimum	295 °C
Min. melt temperature	285 °C
Max. melt temperature	305 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	100 °C
Min. mould temperature	70 °C
Max. mould temperature	120 °C
Hold pressure range	50 - 100 MPa
Ejection temperature	215 °C

Characteristics

Processing	Injection Moulding
Delivery form	Pellets
Special characteristics	Increased electrical conductivity, Heat stabilised or stable to heat, Light weight

CELSTRAN® PA66-CF40-02 AF3004 NATURAL

CELSTRAN® Long Fibre

Additional information

Processing Notes


Pre-Drying

CELSTRAN PA should in principle be predried. Because of the necessary low maximum residual moisture content the use of dry air dryers is recommended. The dew point should be $\leq -30^{\circ}\text{C}$. The time between drying and processing should be as short as possible.

Storage

Note: Material can be over dried and may discolor.


Stress-strain



CELSTRAN® PA66-CF40-02 AF3004 NATURAL

CELSTRAN® Long Fibre

Secant modulus-strain



Printed: 2025-05-29

Page: 3 of 3

Revised: 2025-03-12 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

© 2025 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC.