

CELSTRAN® PA66-GF40-02P11/15

CELSTRAN® Long Fibre

Material code according to ISO 1043-1: PA66

Heat stabilized Nylon 66 reinforced by 40 weight percent long glass fibers. The pellets are cylindrical and normally as well as the embedded fibers 10 mm long.

Parts molded of CELSTRAN have outstanding mechanical properties such as high strength and stiffness combined with high heat deflection. The notched impact strength is increased at elevated and low temperatures due to the fiber skeleton built in the parts. The long fiber reinforcement reduces creep significantly.

The very isotropic shrinkage in the molded parts minimizes the warpage.

Complex parts can be manufactured with high reproducibility by injection molding.

Can be used for substituting die cast metal with the advantage of Weight reduction, no corrosion problems, no post treatment.

Product information

Resin Identification	PA66-LGF40	ISO 1043
Part Marking Code	>PA66-LGF40<	ISO 11469

Rheological properties

	dry/cond.		
Viscosity number	140 / *	cm ³ /g	ISO 307, 1628

Typical mechanical properties

	dry/cond.		
Tensile modulus	13700 / 10000	MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	190 / 160	MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	1.6 / 2	%	ISO 527-1/-2
Flexural modulus	12600 / 10000	MPa	ISO 178
Flexural strength	260 / 250	MPa	ISO 178
Flexural strain at failure	2.2 / 3.2	%	ISO 178
Charpy impact strength, 23°C	40 / 45	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	41 / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	23 / 18	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	23 / -	kJ/m ²	ISO 179/1eA
Izod notched impact strength, 23°C	24 / 18	kJ/m ²	ISO 180/1A
Izod notched impact strength, -30°C	35.0 / -	kJ/m ²	ISO 180/1A
Poisson's ratio	0.33 / 0.34 ^[C]		

[C]: Calculated

Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	261 / *	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	255 / *	°C	ISO 75-1/-2
Temperature of deflection under load, 8 MPa	240 / *	°C	ISO 75-1/-2

Physical/Other properties

	dry/cond.		
Density	1460 / -	kg/m ³	ISO 1183

CELSTRAN® PA66-GF40-02P11/15

CELSTRAN® Long Fibre

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.2 %
Melt Temperature Optimum	295 °C
Min. melt temperature	285 °C
Max. melt temperature	305 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	100 °C
Min. mould temperature	70 °C
Max. mould temperature	120 °C
Hold pressure range	50 - 100 MPa
Back pressure	3 MPa

Characteristics

Processing	Injection Moulding, Extrusion, Sheet Extrusion, Other Extrusion, Transfer Moulding
Delivery form	Pellets
Special characteristics	Heat stabilised or stable to heat

Additional information

Injection molding

Preprocessing

It is recommended to dry in a dehumidifying dryer: 4 hours at 80 °C.

Processing

During the processing of CELSTRAN it is important to watch and control melt shear, for excessive shear reduces fiber length and mechanical performance as well.

Processing recommendation:

- Conventional 3 zone screw, screw diameter minimum 40 mm
- Design flow channels for low melt shear
- Back pressure and screw rotation to realize a continuous plastification performance and thus a homogeneous melt.
- Apply higher temperature settings than for short fiber compounds

Melt temperature (in the screw anteroom) 300-315 °C
Mold surface temperature 90-120 °C

Processing Notes

Pre-Drying


CELSTRAN PA should in principle be predried. Because of the necessary low

CELSTRAN® PA66-GF40-02P11/15

CELSTRAN® Long Fibre

maximum residual moisture content the use of dry air dryers is recommended.
The dew point should be $\leq -30^{\circ}\text{C}$. The time between drying and processing
should be as short as possible.


Stress-strain (dry)



CELSTRAN® PA66-GF40-02P11/15

CELSTRAN® Long Fibre


Stress-strain (cond.)



CELSTRAN® PA66-GF40-02P11/15

CELSTRAN® Long Fibre


Secant modulus-strain (dry)



CELSTRAN® PA66-GF40-02P11/15

CELSTRAN® Long Fibre

Secant modulus-strain (cond.)



Printed: 2025-05-29

Page: 6 of 6

Revised: 2024-04-15 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

© 2025 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC.