

# ECOMID® A HH GF51 ECO-R BK 9004/2

Polyamide 66 compound for injection moulding, 50% glass fibers reinforced, heat stabilized.

*Designed for Automotive industry, suitable for other technical applications that require long term heat ageing resistance.*

## Product information

Part Marking Code

>PA66-GF50(REC30)<

ISO 11469

## Rheological properties

Moulding shrinkage range, parallel

0.2 - 0.5 %

ISO 294-4, 2577

Moulding shrinkage range, normal

0.5 - 0.8 %

ISO 294-4, 2577

## Typical mechanical properties

dry/cond.

Tensile Modulus

16500/-

MPa

ISO 527-1/-2

Stress at break, 5mm/min

200/-

MPa

ISO 527-1/-2

Strain at break, 5mm/min

2/-

%

ISO 527-1/-2

Flexural Modulus

15500/-

MPa

ISO 178

Flexural Strength

300/-

MPa

ISO 178

Charpy impact strength, 23°C

65/-

kJ/m<sup>2</sup>

ISO 179/1eU

Charpy notched impact strength, 23°C

10/-

kJ/m<sup>2</sup>

ISO 179/1eA

Izod notched impact strength, 23°C

10/-

kJ/m<sup>2</sup>

ISO 180/1A

## Thermal properties

Melting temperature, 10°C/min

260 °C

ISO 11357-1/-3

Temp. of deflection under load, 1.8 MPa

244 °C

ISO 75-1/-2

## Other properties

Humidity absorption, 2mm

1.2 %

Sim. to ISO 62

Water absorption, 2mm

4 %

Sim. to ISO 62

Density

1590 kg/m<sup>3</sup>

ISO 1183

## Characteristics

Additives

Contains Recycle

## Additional information

Injection molding

The following conditions apply to a standard injection molding process. Machine temperatures: barrel 265-290°C (PA66), 235-270°C (PA6), nozzle and hot runners up to 300°C (up to 290°C products with flame retardants). Mold temperatures: 60-80°C, (80-100°C highly reinforced grades). Back pressure: typically, 5-10 bar (hydraulic pressure). Temperatures exceeding 300°C and long residence time could lead to additives degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending on the molded part characteristics. For further details, please refer to the document 'Instructions for injection molding' or contact our technical support team.

# ECOMID® A HH GF51 ECO-R BK 9004/2

## Processing Texts

### Injection molding

The following conditions apply to a standard injection molding process. Machine temperatures: barrel 265-290°C (PA66), 235-270°C (PA6), nozzle and hot runners up to 300°C (up to 290°C products with flame retardants). Mold temperatures: 60-80°C, (80-100°C highly reinforced grades). Back pressure: typically, 5-10 bar (hydraulic pressure). Temperatures exceeding 300°C and long residence time could lead to additives degradation and brittleness of the material. In case of gas generation in the melt, please verify moisture content and processing temperatures. Usage of regrind is possible depending on the molded part characteristics. For further details, please refer to the document 'Instructions for injection molding' or contact our technical support team.

### Injection molding Preprocessing

PA materials, stocked in a moisture-proof packaging, can be processed without drying; however, it is always recommended drying the product that comes from a large package (e.g. Octabin). The moisture content suggested for the injection molding process should be lower than 0.15%, according to the grade and to the molded part characteristics. The materials containing flame retardants should have moisture content below 0.10%. Red phosphorous containing grades must always be dried below 0.08%. The drying time depends on the moisture content and the drying conditions. Typically, 4-8 hours at 80-90°C using dehumidified air (dew point of -20°C) are suitable conditions for a starting moisture content of 0.20%-0.40%.

### Injection molding Postprocessing

PA materials reach their final performance with a water content of about 1.5 to 3.5% by weight, depending on the type. This percentage corresponds to the point of equilibrium between the rates of absorption and desorption of moisture. After molding, in favorable environmental conditions, a part can quickly absorb moisture up to 0.5-1.0%, while the equilibrium will be reached during its life. A conditioning treatment can accelerate further the initial water absorption of the molded parts. Conditioning is usually carried out in hot and humid environment (for example 50°C, 100% RH), inside climatic chambers. Slight dimensional variations (increase in volume due to the water absorbed) must be considered, especially in unfilled grades. Post-treatments of parts may also include the annealing (60-80°C in oven, up to four hours). This procedure can be useful to relax any internal stresses.

## Other Approvals

### Other Approvals

OEM	Specification	Additional Information
VW Group*	VW50133	* best fitting grade to PA66-8-A, not officially approved

(+) 18816996168

Ponciplastics.com



# ECOMID® A HH GF51 ECO-R BK 9004/2

VW Group*	VW50127	* best fitting grade to PA66-10, not officially approved
-----------	---------	--

---