

# FRIANYL® A3 RV0 BK 9005/F

## FRIANYL®

*Designed for Electrical applications requiring self-extinguishing properties combined with easy processability and good surface quality, this grade meets the most stringent safety requirements for insulating materials.*

### Product information

Resin Identification	PA66	ISO 1043
Part Marking Code	>PA66<	ISO 11469
Continuous Service Temperature	130 °C	IEC 60216-1

### Rheological properties

	dry/cond.		
Viscosity number	140/*	cm <sup>3</sup> /g	ISO 307, 1628

### Typical mechanical properties

	dry/cond.		
Tensile modulus	3550/-	MPa	ISO 527-1/-2
Tensile stress at yield, 50mm/min	70/-	MPa	ISO 527-1/-2
Tensile strain at break, 50mm/min	3/-	%	ISO 527-1/-2
Charpy impact strength, 23°C	45/-	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23°C	3/-	kJ/m <sup>2</sup>	ISO 179/1eA
Poisson's ratio	0.36/- <sup>[C]</sup>		
[C]: Calculated			

### Thermal properties

	dry/cond.		
Melting temperature, 10°C/min	260/*	°C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	85/*	°C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	185/*	°C	ISO 75-1/-2

### Flammability

	dry/cond.		
Burning Behav. at 1.5mm nom. thickn.	V-0/*	class	IEC 60695-11-10
Burning Behav. at thickness h	V-0/*	class	IEC 60695-11-10
Thickness tested	0.4/*	mm	IEC 60695-11-10
Glow Wire Flammability Index, 0.75mm	960/-	°C	IEC 60695-2-12
Glow Wire Flammability Index, 3.0mm	960/-	°C	IEC 60695-2-12

### Electrical properties

Comparative tracking index, 100 drops	600	IEC 60112
---------------------------------------	-----	-----------

### Physical/Other properties

	dry/cond.		
Density	1170/-	kg/m <sup>3</sup>	ISO 1183

### Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.1 %
Melt Temperature Optimum	275 °C
Min. melt temperature	265 °C
Max. melt temperature	285 °C

# FRIANYL® A3 RV0 BK 9005/F

## FRIANYL®

Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	70 °C
Min. mould temperature	60 °C
Max. mould temperature	90 °C

## Characteristics

Processing	Injection Moulding
Delivery form	Granules
Additives	Flame retardant, Non-halogenated/Red phosphorous free flame retardant
Special characteristics	Flame retardant, Heat stabilised or stable to heat

## Automotive

OEM	STANDARD	ADDITIONAL INFORMATION
VW Group	VW 50133	*Best Fitting Grade To PA66-1-A, Not Officially Approved