

# FRIANYL® A3 W GF30 V0E BK 9005

## FRIANYL®

*Designed for Electrical applications requiring self-extinguishing properties combined with good mechanical performances, this grade meets the most stringent safety requirements for insulating materials. Ideal for thicker walled parts.*

### Product information

Resin Identification	(PA66+PA6)-GF30FR(40)	ISO 1043
Part Marking Code	>(PA66+PA6)-GF30FR(40)<	ISO 11469
Continuous Service Temperature	130 °C	IEC 60216-1

### Rheological properties

Moulding shrinkage range, parallel	0.3 - 0.6 %	ISO 294-4, 2577
Moulding shrinkage range, normal	0.6 - 0.9 %	ISO 294-4, 2577

### Typical mechanical properties

	dry/cond.		
Tensile modulus	10500 / 6500	MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	150 / 100	MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	2.5 / 5	%	ISO 527-1/-2
Charpy impact strength, 23 °C	60 / 60	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30 °C	55 / 55	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23 °C	9 / 15	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30 °C	7.5 / 7.5	kJ/m <sup>2</sup>	ISO 179/1eA
Poisson's ratio	0.34 / 0.35 <sup>[C]</sup>		
[C]: Calculated			

### Thermal properties

	dry/cond.		
Melting temperature, 10 °C/min	260 / *	°C	ISO 11357-1/-3

### Flammability

	dry/cond.		
Burning Behav. at 1.5mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
UL recognition	yes / *		UL 94
Burning Behav. at thickness h	V-0 / *	class	IEC 60695-11-10
Thickness tested	3 / *	mm	IEC 60695-11-10
UL recognition	yes / *		UL 94
Glow Wire Flammability Index, 0.75mm	960 / -	°C	IEC 60695-2-12
Glow Wire Flammability Index, 3.0mm	960 / -	°C	IEC 60695-2-12

### Electrical properties

	dry/cond.		
Volume resistivity	1E14 / -	Ohm.m	IEC 62631-3-1
Surface resistivity	* / 1E13	Ohm	IEC 62631-3-2
Electric strength	45 / -	kV/mm	IEC 60243-1
Electric strength, Direct Current	18.7	kV/mm	IEC 60243-2
Comparative tracking index, 100 drops	600		IEC 60112

# FRIANYL® A3 W GF30 V0E BK 9005

## FRIANYL®

### Physical/Other properties

	dry/cond.		
Humidity absorption, 2mm	1.4 / *	%	Sim. to ISO 62
Water absorption, 2mm	4.9 / *	%	Sim. to ISO 62
Density	1410 / -	kg/m <sup>3</sup>	ISO 1183


### Characteristics

Processing	Injection Moulding
Delivery form	Granules
Additives	Flame retardant, Non-halogenated/Red phosphorous free flame retardant, Low halide content
Special characteristics	Flame retardant, Heat stabilised or stable to heat, Thermal shock resistant

# FRIANYL® A3 W GF30 V0E BK 9005

FRIANYL®


## Stress-strain (dry)



# FRIANYL® A3 W GF30 V0E BK 9005

FRIANYL®


## Stress-strain (cond.)



# FRIANYL® A3 W GF30 V0E BK 9005

FRIANYL®


## Secant modulus-strain (dry)



# FRIANYL® A3 W GF30 V0E BK 9005

## FRIANYL®

### Secant modulus-strain (cond.)



Printed: 2025-05-29

Page: 6 of 6

Revised: 2025-02-14 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

© 2025 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC.