

Crastin® SK609 NC010

THERMOPLASTIC POLYESTER RESIN

Common features of Crastin® thermoplastic polyester resin include mechanical and physical properties such as stiffness and toughness, heat resistance, friction and wear resistance, excellent surface finishes and good colourability. Crastin® thermoplastic polyester resin has excellent electrical insulation characteristics and high arc-resistant grades are available. Many flame retardant grades have UL recognition (class V-0). Crastin® thermoplastic polyester resin typically has high chemical and heat ageing resistance.

The good melt stability of Crastin® thermoplastic polyester resin normally enables the recycling of properly handled production waste. If recycling is not possible, we recommend, as the preferred option, incineration with energy recovery (-24 kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Crastin® thermoplastic polyester resin typically is used in demanding applications in the electronics, electrical, automotive, mechanical engineering, chemical, domestic appliances and sporting goods industry.

Crastin® SK609 NC010 is a 50% glass fiber reinforced, lubricated polybutylene terephthalate resin for injection moulding.

Product information

| | | |
|----------------------|------------|-----------|
| Resin Identification | PBT-GF50 | ISO 1043 |
| Part Marking Code | >PBT-GF50< | ISO 11469 |

Rheological properties

| | | |
|---|--------------------------|-----------------|
| Melt volume-flow rate | 2 cm ³ /10min | ISO 1133 |
| Temperature | 250 °C | |
| Load | 2.16 kg | |
| Melt mass-flow rate | 3 g/10min | ISO 1133 |
| Melt mass-flow rate, Temperature | 250 °C | |
| Melt mass-flow rate, Load | 2.16 kg | |
| Moulding shrinkage, parallel | 0.3 % | ISO 294-4, 2577 |
| Moulding shrinkage, normal | 1.1 % | ISO 294-4, 2577 |
| Postmoulding shrinkage, normal, 48h at 80°C | 0.2 % | ISO 294-4 |
| Postmoulding shrinkage, parallel, 48h at 80°C | 0.1 % | ISO 294-4 |

Typical mechanical properties

| | | |
|---------------------------------------|------------------------|--------------|
| Tensile modulus | 16000 MPa | ISO 527-1/-2 |
| Tensile stress at break, 5mm/min | 160 MPa | ISO 527-1/-2 |
| Tensile strain at break, 5mm/min | 1.7 % | ISO 527-1/-2 |
| Flexural modulus | 15000 MPa | ISO 178 |
| Flexural strength | 230 MPa | ISO 178 |
| Tensile creep modulus, 1h | 15000 MPa | ISO 899-1 |
| Tensile creep modulus, 1000h | 11600 MPa | ISO 899-1 |
| Charpy impact strength, 23°C | 55 kJ/m ² | ISO 179/1eU |
| Charpy impact strength, -30°C | 65 kJ/m ² | ISO 179/1eU |
| Charpy notched impact strength, 23°C | 11 kJ/m ² | ISO 179/1eA |
| Charpy notched impact strength, -30°C | 12 kJ/m ² | ISO 179/1eA |
| Izod notched impact strength, 23°C | 10 kJ/m ² | ISO 180/1A |
| Izod notched impact strength, -30°C | 10.0 kJ/m ² | ISO 180/1A |
| Izod impact strength, 23°C | 43 kJ/m ² | ISO 180/1U |
| Izod impact strength, -30°C | 43 kJ/m ² | ISO 180/1U |

Crastin® SK609 NC010

THERMOPLASTIC POLYESTER RESIN

Poisson's ratio 0.33

Thermal properties

| | | |
|--|---------------|----------------|
| Melting temperature, 10°C/min | 224 °C | ISO 11357-1/-3 |
| Glass transition temperature, 10°C/min | 55 °C | ISO 11357-1/-3 |
| Temperature of deflection under load, 1.8 MPa | 210 °C | ISO 75-1/-2 |
| Temperature of deflection under load, 0.45 MPa | 222 °C | ISO 75-1/-2 |
| Vicat softening temperature, 50°C/h 50N | 215 °C | ISO 306 |
| Coefficient of linear thermal expansion (CLTE), parallel | 20 E-6/K | ISO 11359-1/-2 |
| Coefficient of linear thermal expansion (CLTE), normal | 80 E-6/K | ISO 11359-1/-2 |
| Thermal conductivity of melt | 0.36 W/(m K) | ISO 22007-2 |
| Specific heat capacity of melt | 1470 J/(kg K) | ISO 22007-4 |
| RTI, electrical, 0.75mm | 130 °C | UL 746B |
| RTI, electrical, 1.5mm | 130 °C | UL 746B |
| RTI, electrical, 3.0mm | 130 °C | UL 746B |
| RTI, electrical, 6mm | 130 °C | UL 746B |
| RTI, impact, 0.75mm | 125 °C | UL 746B |
| RTI, impact, 1.5mm | 125 °C | UL 746B |
| RTI, impact, 3.0mm | 125 °C | UL 746B |
| RTI, impact, 6mm | 125 °C | UL 746B |
| RTI, strength, 0.75mm | 130 °C | UL 746B |
| RTI, strength, 1.5mm | 130 °C | UL 746B |
| RTI, strength, 3.0mm | 130 °C | UL 746B |
| RTI, strength, 6mm | 130 °C | UL 746B |

Flammability

| | | |
|--------------------------------------|-----------|----------------------|
| Burning Behav. at 1.5mm nom. thickn. | HB class | IEC 60695-11-10 |
| Thickness tested | 1.5 mm | IEC 60695-11-10 |
| UL recognition | yes | UL 94 |
| Burning Behav. at thickness h | HB class | IEC 60695-11-10 |
| Thickness tested | 0.75 mm | IEC 60695-11-10 |
| UL recognition | yes | UL 94 |
| Oxygen index | 20 % | ISO 4589-1/-2 |
| Glow Wire Flammability Index, 3.0mm | 750 °C | IEC 60695-2-12 |
| FMVSS Class | B | ISO 3795 (FMVSS 302) |
| Burning rate, Thickness 1 mm | 27 mm/min | ISO 3795 (FMVSS 302) |

Electrical properties

| | | |
|------------------------------------|-------------|---------------|
| Relative permittivity, 100Hz | 4.1 | IEC 62631-2-1 |
| Relative permittivity, 1MHz | 3.9 | IEC 62631-2-1 |
| Dissipation factor, 100Hz | 38 E-4 | IEC 62631-2-1 |
| Dissipation factor, 1MHz | 130 E-4 | IEC 62631-2-1 |
| Volume resistivity | >1E13 Ohm.m | IEC 62631-3-1 |
| Electric strength | 33 kV/mm | IEC 60243-1 |
| Comparative tracking index | 500 | IEC 60112 |
| Electric Strength, Short Time, 2mm | 14 kV/mm | IEC 60243-1 |

Crastin® SK609 NC010

THERMOPLASTIC POLYESTER RESIN

Physical/Other properties

| | | |
|--------------------------|------------------------|----------------|
| Humidity absorption, 2mm | 0.1 % | Sim. to ISO 62 |
| Water absorption, 2mm | 0.2 % | Sim. to ISO 62 |
| Density | 1720 kg/m ³ | ISO 1183 |
| Density of melt | 1600 kg/m ³ | |

VDA Properties

| | | |
|-------------------------------|------|----------|
| Fogging, G-value (condensate) | 0 mg | ISO 6452 |
|-------------------------------|------|----------|

Injection

| | |
|---------------------------------|--------------------|
| Drying Recommended | yes |
| Drying Temperature | 120 °C |
| Drying Time, Dehumidified Dryer | 2 - 4 h |
| Processing Moisture Content | ≤0.04 % |
| Melt Temperature Optimum | 260 °C |
| Min. melt temperature | 250 °C |
| Max. melt temperature | 270 °C |
| Mold Temperature Optimum | 80 °C |
| Min. mould temperature | 60 °C |
| Max. mould temperature | 130 °C |
| Hold pressure range | ≥60 MPa |
| Hold pressure time | 3 s/mm |
| Back pressure | As low as possible |
| Ejection temperature | 180 °C |


Characteristics

| | |
|---------------|--------------------|
| Processing | Injection Moulding |
| Delivery form | Pellets |
| Additives | Release agent |

Crastin® SK609 NC010

THERMOPLASTIC POLYESTER RESIN


Viscosity-shear rate



Crastin® SK609 NC010

THERMOPLASTIC POLYESTER RESIN


Shearstress-shear rate



Crastin® SK609 NC010

THERMOPLASTIC POLYESTER RESIN


Stress-strain



Crastin® SK609 NC010

THERMOPLASTIC POLYESTER RESIN


Secant modulus-strain



Crastin® SK609 NC010

THERMOPLASTIC POLYESTER RESIN


Stress-strain (isochronous) 23°C



Crastin® SK609 NC010

THERMOPLASTIC POLYESTER RESIN


Creep modulus-time 23°C



Crastin® SK609 NC010

THERMOPLASTIC POLYESTER RESIN


Stress-strain (isochronous) 60°C



Crastin® SK609 NC010

THERMOPLASTIC POLYESTER RESIN


Creep modulus-time 60°C



Crastin® SK609 NC010

THERMOPLASTIC POLYESTER RESIN


Stress-strain (isochronous) 90°C



Crastin® SK609 NC010

THERMOPLASTIC POLYESTER RESIN

Creep modulus-time 90°C



Crastin® SK609 NC010

THERMOPLASTIC POLYESTER RESIN

Chemical Media Resistance

Acids

- ✓ Acetic Acid (5% by mass), 23°C
- ✓ Citric Acid solution (10% by mass), 23°C
- ✓ Lactic Acid (10% by mass), 23°C
- ✗ Hydrochloric Acid (36% by mass), 23°C
- ✗ Nitric Acid (40% by mass), 23°C
- ✗ Sulfuric Acid (38% by mass), 23°C
- ✗ Sulfuric Acid (5% by mass), 23°C
- ✗ Chromic Acid solution (40% by mass), 23°C

Bases

- ✗ Sodium Hydroxide solution (35% by mass), 23°C
- ✓ Sodium Hydroxide solution (1% by mass), 23°C
- ✓ Ammonium Hydroxide solution (10% by mass), 23°C

Alcohols

- ✓ Isopropyl alcohol, 23°C
- ✓ Methanol, 23°C
- ✓ Ethanol, 23°C

Hydrocarbons

- ✓ n-Hexane, 23°C
- ✓ Toluene, 23°C
- ✓ iso-Octane, 23°C

Ketones

- ✓ Acetone, 23°C

Ethers

- ✓ Diethyl ether, 23°C

Mineral oils

- ✓ SAE 10W40 multigrade motor oil, 23°C
- ✗ SAE 10W40 multigrade motor oil, 130°C
- ✗ SAE 80/90 hypoid-gear oil, 130°C
- ✓ Insulating Oil, 23°C

Standard Fuels

- ✗ ISO 1817 Liquid 1 - E5, 60°C
- ✗ ISO 1817 Liquid 2 - M15E4, 60°C
- ✗ ISO 1817 Liquid 3 - M3E7, 60°C
- ✗ ISO 1817 Liquid 4 - M15, 60°C
- ✓ Standard fuel without alcohol (pref. ISO 1817 Liquid C), 23°C
- ✓ Standard fuel with alcohol (pref. ISO 1817 Liquid 4), 23°C
- ✓ Diesel fuel (pref. ISO 1817 Liquid F), 23°C
- ✓ Diesel fuel (pref. ISO 1817 Liquid F), 90°C
- ✗ Diesel fuel (pref. ISO 1817 Liquid F), >90°C

Salt solutions

- ✓ Sodium Chloride solution (10% by mass), 23°C
- ✓ Sodium Hypochlorite solution (10% by mass), 23°C

Crastin® SK609 NC010

THERMOPLASTIC POLYESTER RESIN

- ✓ Sodium Carbonate solution (20% by mass), 23 °C
- ✓ Sodium Carbonate solution (2% by mass), 23 °C
- ✓ Zinc Chloride solution (50% by mass), 23 °C

Other

- ✓ Ethyl Acetate, 23 °C
- ✗ Hydrogen peroxide, 23 °C
- ✗ DOT No. 4 Brake fluid, 130 °C
- ✗ Ethylene Glycol (50% by mass) in water, 108 °C
- ✓ 1% nonylphenoxy-polyethyleneoxy ethanol in water, 23 °C
- ✓ 50% Oleic acid + 50% Olive Oil, 23 °C
- ✓ Water, 23 °C
- ✗ Water, 90 °C
- ✓ Phenol solution (5% by mass), 23 °C

Symbols used:

- ✓ possibly resistant
Defined as: Supplier has sufficient indication that contact with chemical can be potentially accepted under the intended use conditions and expected service life. Criteria for assessment have to be indicated (e.g. surface aspect, volume change, property change).
- ✗ not recommended - see explanation
Defined as: Not recommended for general use. However, short-term exposure under certain restricted conditions could be acceptable (e.g. fast cleaning with thorough rinsing, spills, wiping, vapor exposure).