

PIBITER N200LP NERO900 - PBT

Physical properties	Value	Unit	Test Standard
Density	1320	kg/m ³	ISO 1183
Melt flow rate, MFR	25	g/10min	ISO 1133
MFR temperature	250	°C	ISO 1133
MFR load	2.16	kg	ISO 1133

Mechanical properties	Value	Unit	Test Standard
Tensile modulus	2400	MPa	ISO 527-2/1A
Tensile stress at yield, 50mm/min	50	MPa	ISO 527-2/1A
Tensile strain at yield, 50mm/min	>5	%	ISO 527-2/1A
Tensile stress at break, 50mm/min	>20	MPa	ISO 527-2/1A
Tensile strain at break, 50mm/min	>10	%	ISO 527-2/1A
Charpy notched impact strength, 23°C	2	kJ/m ²	ISO 179/1eA

Characteristics

Product Categories

Unfilled