

VANDAR® 2500 - PBT
Description

Unreinforced, high impact, good colorability

Vandar 2500 is an unfilled polyester alloy which exhibits excellent toughness and impact strength. It is specially designed to offer excellent chemical resistance, good colorability and dimensional stability.

Physical properties	Value	Unit	Test Standard
Density	78	lb/ft³	ISO 1183
Melt flow rate, MFR	13	g/10min	ISO 1133
MFR temperature	482	°F	ISO 1133
MFR load	11	lb	ISO 1133
Molding shrinkage, parallel (flow)	1.7 - 2.2	%	ISO 294-4, 2577
Molding shrinkage, transverse normal	1.7 - 2.2	%	ISO 294-4, 2577
Water absorption, 23°C-sat	0.45	%	Sim. to ISO 62

Mechanical properties	Value	Unit	Test Standard
Tensile modulus	210305	psi	ISO 527-1, -2
Tensile stress at yield, 50mm/min	5080	psi	ISO 527-1, -2
Tensile strain at yield, 50mm/min	5	%	ISO 527-1, -2
Tensile nominal strain at break, 50mm/min	>50	%	ISO 527-1, -2
Flexural modulus, 23°C	218000	psi	ISO 178
Flexural strength, 23°C	7250	psi	ISO 178
Charpy impact strength, 23°C	96.6	ft-lb/in²	ISO 179/1eU
Charpy impact strength, -30°C	79.9	ft-lb/in²	ISO 179/1eU
Charpy notched impact strength, 23°C	41.9	ft-lb/in²	ISO 179/1eA
Charpy notched impact strength, -30°C	4.28	ft-lb/in²	ISO 179/1eA
Izod impact notched, 23°C	NB	ft-lb/in²	ISO 180/1A
Rockwell hardness (M-Scale)	104	M-Scale	ISO 2039-2

Thermal properties	Value	Unit	Test Standard
Melting temperature, 10°C/min	437	°F	ISO 11357-1/-3
Glass transition temperature, 10°C/min	158	°F	ISO 11357-1,-2,-3
DTUL at 1.8 MPa	122	°F	ISO 75-1, -2
DTUL at 0.45 MPa	257	°F	ISO 75-1, -2
Coeff. of linear therm expansion, parallel	0.722	E-4/°F	ISO 11359-2
Coeff. of linear therm expansion, normal	0.744	E-4/°F	ISO 11359-2

Typical injection moulding processing conditions

Pre Drying	Value	Unit
Necessary low maximum residual moisture content	0.02	%
Drying time	4	h
Drying temperature	248 - 266	°F

Temperature	Value	Unit
Hopper temperature	68 - 122	°F
Feeding zone temperature	446 - 464	°F
Zone1 temperature	446 - 464	°F
Zone2 temperature	455 - 482	°F
Zone3 temperature	455 - 482	°F
Zone4 temperature	464 - 500	°F
Nozzle temperature	464 - 500	°F
Melt temperature	455 - 500	°F
Mold temperature	149 - 205	°F
Hot runner temperature	482 - 500	°F

VANDAR® 2500 - PBT**Speed****Value**

Injection speed

medium-fast**Other text information****Pre-drying**

To avoid hydrolytic degradation during processing, Vandar resins have to be dried to a moisture level equal to or less than 0.02%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-40 °F (-40 °C) at 250 °F (121 °C) for 4 hours.

Longer pre-drying times/storage

For subsequent storage of the material in the dryer until processed (<= 60 h) it is necessary to lower the temperature to 100 ° C.

Injection molding

Rear Temperature 450-480(230-250) deg F (deg C)
Center Temperature 460-490(235-255) deg F (deg C)
Front Temperature 470-500(240-260) deg F (deg C)
Nozzle Temperature 470-510(240-265) deg F (deg C)
Melt Temperature 470-510(240-265) deg F (deg C)
Mold Temperature 100-200(40-95 deg F (deg C)
Back Pressure 0-50 psi
Screw Speed Moderate
Injection Speed Fast

Injection speed, injection pressure and holding pressure have to be optimized to the individual article geometry. To avoid material degradation during processing low back pressure and minimum screw speed have to be used. Overheating of the material has to be avoided, in particular for flame retardant grades. Up to 25% clean and dry regrind may be used.

Injection Molding Preprocessing

To avoid hydrolytic degradation during processing, Vandar resins have to be dried to a moisture level equal to or less than 0.02%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-30 °F (-34 °C) at 250 °F (121 °C) for 4 hours.

Characteristics

Special Characteristics	Auto spec approved
Product Categories	Impact modified, Unfilled
Processing	Injection molding
Delivery Form	Pellets
Additives	Lubricants

Other Approvals

OEM	Specification	Additional Information
Stellantis - Chrysler	CPN 2724	Black