

CELANEX® 2302 GV1/30 - PBT
Description

PBT + PET, 30% glass filled, high gloss

Chemical abbreviation according to ISO 1043-1: PBT Moulding compound ISO 7792- PBT+PET, MGHR, 08-110N, GF30; Polybutylene terephthalate polymer blend with PET, 30 % glass fibre reinforced, injection molded parts with superior gloss. Flammability UL 94 HB minimum thickness 0.82 mm. Recognition by Underwriters Laboratories, USA (UL)

Physical properties	Value	Unit	Test Standard
Density	96.8	lb/ft ³	ISO 1183
Melt volume rate, MVR	14	cm ³ /10min	ISO 1133
MVR temperature	509	°F	ISO 1133
MVR load	4.76	lb	ISO 1133
Molding shrinkage, parallel (flow)	0.2 - 0.3	%	ISO 294-4, 2577
Molding shrinkage, transverse normal	0.6 - 0.8	%	ISO 294-4, 2577
Water absorption, 23°C-sat	0.4	%	Sim. to ISO 62
Humidity absorption, 23°C/50%RH	0.15	%	ISO 62
Mechanical properties	Value	Unit	Test Standard
Tensile modulus	1.52E6	psi	ISO 527-1, -2
Tensile stress at break, 5mm/min	21800	psi	ISO 527-1, -2
Tensile strain at break, 5mm/min	2.5	%	ISO 527-1, -2
Flexural strength, 23°C	30500	psi	ISO 178
Charpy impact strength, 23°C	26.6	ft-lb/in ²	ISO 179/1eU
Charpy impact strength, -30°C	27.6	ft-lb/in ²	ISO 179/1eU
Charpy notched impact strength, 23°C	4.76	ft-lb/in ²	ISO 179/1eA
Izod impact unnotched, -30°C	4.28	ft-lb/in ²	ISO 180/1U
Ball indentation hardness, 30s	31900	psi	ISO 2039-1
Thermal properties	Value	Unit	Test Standard
Melting temperature, 10°C/min	491	°F	ISO 11357-1/-3
DTUL at 1.8 MPa	392	°F	ISO 75-1, -2
DTUL at 0.45 MPa	428	°F	ISO 75-1, -2
DTUL at 8.0 MPa	257	°F	ISO 75-1, -2
Vicat softening temperature, 50°C/h 50N	437	°F	ISO 306
Coeff. of linear therm expansion, parallel	0.111	E-4/°F	ISO 11359-2
Limiting oxygen index (LOI)	20	%	ISO 4589-1/-2
Flammability @1.6mm nom. thickn.	HB	class	UL 94
thickness tested (1.6)	0.1	in	UL 94
Flammability at thickness h	HB	class	UL 94
thickness tested (h)	0.0323	in	UL 94
UL recognition (h)	UL	-	UL 94
Electrical properties	Value	Unit	Test Standard
Dielectric constant (Dk), 100Hz	4.4	-	IEC 60250
Dielectric constant (Dk), 1MHz	4.1	-	IEC 60250
Dissipation factor, 100Hz	14	E-4	IEC 60250
Dissipation factor, 1MHz	170	E-4	IEC 60250
Volume resistivity, 23°C	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity, 23°C	>1E15	Ohm	IEC 62631-3-2
Electric strength, 23°C (AC)	787	kV/in	IEC 60243-1
Comparative tracking index	PLC 2	-	UL 746
CTI 50 drops	250	V	IEC 60112
Rheological calculation properties	Value	Unit	Test Standard
Density of melt	82.4	lb/ft ³	Internal
Thermal conductivity of melt	0.171	W/(m K)	Internal
Spec. heat capacity melt	1730	J/(kg K)	Internal

Ejection temperature

428



°F

Internal

Diagrams



Viscosity-shear rate

Shear stress-shear rate





Dynamic Shear modulus-temperature

Stress-strain





Secant modulus-strain

True Stress-strain



CAMPUS Stress-strain (isochronous) 73.4 °F

CAMPUS Creep modulus-time 73.4 °F



Typical injection moulding processing conditions

Pre Drying

Necessary low maximum residual moisture content
Drying time
Drying temperature

Value Unit

0.02 %
2 - 4 h
248 - 284 °F

CELANEX® 2302 GV1/30 - PBT

Temperature	Value	Unit
Hopper temperature	68 - 122	°F
Feeding zone temperature	446 - 464	°F
Zone1 temperature	482 - 500	°F
Zone2 temperature	482 - 500	°F
Zone3 temperature	500 - 518	°F
Zone4 temperature	500 - 518	°F
Nozzle temperature	509 - 527	°F
Melt temperature	509 - 527	°F
Mold temperature	194 - 248	°F
Hot runner temperature	509 - 527	°F

Speed	Value
Injection speed	fast

Screw Speed	Value	Unit
Screw speed diameter, 25mm	90	RPM
Screw speed diameter, 40mm	75	RPM
Screw speed diameter, 55mm	60	RPM

Other text information**Pre-drying**

CELANEX should in principle be predried. Because of the necessary low maximum residual moisture content the use of dry air dryers is recommended. The dew point should be $\leq -30^{\circ}\text{C}$. The time between drying and processing should be as short as possible.

Longer pre-drying times/storage

For subsequent storage of the material in the dryer until processed ($\leq 60\text{ h}$) it is necessary to lower the temperature to 100°C .

Injection molding

Melt Temperature 265-275 °C
 Mold Temperature *) 90-100 °C
 Maximum Barrel Residence Time **) 5-10 min
 Injection Speed fast
 Peripheral screw speed max.0,3 m/sec
 Back Pressure 10-30 bar
 Injection Pressure 600-1000 bar
 Holding Pressure 400-800 bar
 Nozzle Design open design preferred

Injection speed, injection pressure and holding pressure have to be optimized to the individual article geometry. To avoid material degradation during processing low back pressure and minimum screw speed have to be used. Overheating of the material has to be avoided.

Celanese recommends only externally heated hot runner systems.

*) For moulded parts with especially high requirements to the surface quality or dimensional stability, a mold temperature of up to 110°C can be advantageous.

**) If the cylinder temperatures are higher than the recommended maximum temperatures, the max. residence time in the barrel has to be reduced.

Injection Molding Preprocessing

To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level equal to or less than 0,02%. The drying should be done in a dry-air dryer (dew point $< -30^{\circ}\text{C}$) with a temperature of 120 to 140°C and a drying time of 2 to 4 hours. In case of longer residence times in the dry-air dryer, the temperature should be reduced to 100°C . The time between drying and processing should be kept as short as possible. The processing machine feed hopper should be closed during the processing operation.

Characteristics

Special Characteristics Auto spec approved, Heat resistant, High gloss

(+) 18816996168

CELANEX® 2302 GV1/30 - PBT

Ponciplastics.com

Product Categories	Glass reinforced, Polymer blend
Processing	Injection molding
Delivery Form	Pellets
Additives	Release agent

Other Approvals

OEM	Specification	Additional Information
Bosch	N28 BN08-GF013	Natural & Black
Stellantis - Chrysler	CPN 4314	Black
FAW Group	JF03-28	Black
GM	GMW16733P-PBT-GF30	Black
Great Wall Motor	PBT+PET-GF30	Black 10/0907 (EC24 B-pillar external panel)
Li Auto	Q/LiA5310038	10/0907 Black 2021 (V2)
Renault	EP09a	PMR2020, 10/0900
Renault	EP11b	PMR2020, 10/0900
Renault	IP07a	PMR2020, 10/0900
SAIC Motor	SMTc 5 310 018	10/0907 BLACK