

# CELANEX® 5300-2

30% glass-fiber reinforced PBT+PET blend; high gloss; general purpose; lubricated grade

Celanex 5300-2 is a 30% fiberglass reinforced polyester with improved surface finish. Celanex 5300-2 contains an internal lubricant.

## Product information

|                   |                    |           |
|-------------------|--------------------|-----------|
| Part Marking Code | (PET+PBT)-GF3<br>0 | ISO 11469 |
|-------------------|--------------------|-----------|

## Rheological properties

|                                    |                           |                     |
|------------------------------------|---------------------------|---------------------|
| Melt volume-flow rate              | 20 cm <sup>3</sup> /10min | ISO 1133            |
| Temperature                        | 265 °C                    |                     |
| Load                               | 2.16 kg                   |                     |
| Viscosity number                   | 68 cm <sup>3</sup> /g     | ISO 307, 1157, 1628 |
| Moulding shrinkage range, parallel | 0.3 - 0.5 %               | ISO 294-4, 2577     |

## Typical mechanical properties

|                                       |                       |              |
|---------------------------------------|-----------------------|--------------|
| Tensile Modulus                       | 10000 MPa             | ISO 527-1/-2 |
| Stress at break, 5mm/min              | 135 MPa               | ISO 527-1/-2 |
| Strain at break, 5mm/min              | 3 %                   | ISO 527-1/-2 |
| Flexural Modulus                      | 9000 MPa              | ISO 178      |
| Flexural Strength                     | 200 MPa               | ISO 178      |
| Charpy impact strength, 23°C          | 49 kJ/m <sup>2</sup>  | ISO 179/1eU  |
| Charpy impact strength, -30°C         | 48 kJ/m <sup>2</sup>  | ISO 179/1eU  |
| Charpy notched impact strength, 23°C  | 9.5 kJ/m <sup>2</sup> | ISO 179/1eA  |
| Charpy notched impact strength, -30°C | 9 kJ/m <sup>2</sup>   | ISO 179/1eA  |
| Izod notched impact strength, 23°C    | 8.3 kJ/m <sup>2</sup> | ISO 180/1A   |
| Hardness, Rockwell, M-scale           | 93                    | ISO 2039-2   |

## Thermal properties

|                                             |          |                |
|---------------------------------------------|----------|----------------|
| Melting temperature, 10°C/min               | 250 °C   | ISO 11357-1/-3 |
| Glass transition temperature, 10°C/min      | 60 °C    | ISO 11357-1/-3 |
| Temp. of deflection under load, 1.8 MPa     | 200 °C   | ISO 75-1/-2    |
| Temp. of deflection under load, 0.45 MPa    | 220 °C   | ISO 75-1/-2    |
| Temp. of deflection under load, 8 MPa       | 120 °C   | ISO 75-1/-2    |
| Vicat softening temperature, 50°C/h, 50N    | 225 °C   | ISO 306        |
| Coeff. of linear therm. expansion, parallel | 24 E-6/K | ISO 11359-1/-2 |
| Coeff. of linear therm. expansion, normal   | 75 E-6/K | ISO 11359-1/-2 |

## Flammability

|                               |          |               |
|-------------------------------|----------|---------------|
| Burning Behav. at thickness h | HB class | UL 94         |
| Thickness tested              | 0.71 mm  | UL 94         |
| Oxygen index                  | 20 %     | ISO 4589-1/-2 |

# CELANEX® 5300-2

## Electrical properties

|                              |             |               |
|------------------------------|-------------|---------------|
| Relative permittivity, 100Hz | 4.6         | IEC 62631-2-1 |
| Relative permittivity, 1MHz  | 4.2         | IEC 62631-2-1 |
| Volume resistivity           | >1E13 Ohm.m | IEC 62631-3-1 |
| Surface resistivity          | >1E15 Ohm   | IEC 62631-3-2 |
| Electric strength            | 30 kV/mm    | IEC 60243-1   |
| Comparative tracking index   | PLC 2 PLC   | UL 746A       |

## Other properties

|                          |                        |                |
|--------------------------|------------------------|----------------|
| Humidity absorption, 2mm | 0.2 %                  | Sim. to ISO 62 |
| Water absorption, 2mm    | 0.4 %                  | Sim. to ISO 62 |
| Density                  | 1540 kg/m <sup>3</sup> | ISO 1183       |

## Injection

|                                 |              |
|---------------------------------|--------------|
| Drying Temperature              | 120 - 130 °C |
| Drying Time, Dehumidified Dryer | 4 h          |
| Processing Moisture Content     | 0.02 %       |
| Max. mould temperature          | 65 - 93 °C   |
| Injection speed                 | medium-fast  |

## Processing Texts

|                                 |                                                                                                                                                                                                                                                             |
|---------------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Pre-drying                      | To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level equal to or less than 0.02%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-40°F (-40°C) at 250°F (121°C) for 4 hours. |
| Longer pre-drying times/storage | For subsequent storage of the material in the dryer until processed (<= 60 h) it is necessary to lower the temperature to 100° C.                                                                                                                           |