

CELANEX® 5300

30% glass-fiber reinforced PBT+PET blend; high gloss; general purpose grade

30% glass reinforced, high gloss, general purpose.

Celanex 5300 is a 30% fiberglass reinforced polyester with improved surface finish.

Product information

Part Marking Code	(PET+PBT)-GF3 0	ISO 11469
-------------------	--------------------	-----------

Rheological properties

Melt volume-flow rate	20 cm ³ /10min	ISO 1133
Temperature	265 °C	
Load	2.16 kg	
Moulding shrinkage range, parallel	0.3 - 0.5 %	ISO 294-4, 2577

Typical mechanical properties

Tensile Modulus	10000 MPa	ISO 527-1/-2
Stress at break, 5mm/min	135 MPa	ISO 527-1/-2
Strain at break, 5mm/min	3 %	ISO 527-1/-2
Flexural Modulus	9000 MPa	ISO 178
Flexural Strength	200 MPa	ISO 178
Charpy impact strength, 23°C	49 kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	48 kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	9.5 kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	9 kJ/m ²	ISO 179/1eA
Izod notched impact strength, 23°C	8.3 kJ/m ²	ISO 180/1A
Hardness, Rockwell, M-scale	93	ISO 2039-2

Thermal properties

Melting temperature, 10°C/min	225 °C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	60 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	200 °C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	220 °C	ISO 75-1/-2
Temp. of deflection under load, 8 MPa	120 °C	ISO 75-1/-2
Vicat softening temperature, 50°C/h, 50N	225 °C	ISO 306
Coeff. of linear therm. expansion, parallel	24 E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	75 E-6/K	ISO 11359-1/-2

CELANEX® 5300

Flammability

Burning Behav. at thickness h	HB class	UL 94
Thickness tested	0.71 mm	UL 94
Oxygen index	20 %	ISO 4589-1/-2

Electrical properties

Relative permittivity, 100Hz	4.6	IEC 62631-2-1
Volume resistivity	>1E13 Ohm.m	IEC 62631-3-1
Surface resistivity	>1E15 Ohm	IEC 62631-3-2
Electric strength	30 kV/mm	IEC 60243-1
Comparative tracking index M	Group IIIa ^[1]	IEC 60112
[1]: 100 drops		

Other properties

Humidity absorption, 2mm	0.2 %	Sim. to ISO 62
Water absorption, 2mm	0.4 %	Sim. to ISO 62
Density	1540 kg/m ³	ISO 1183

Injection

Drying Temperature	120 - 130 °C
Drying Time, Dehumidified Dryer	4 h
Processing Moisture Content	0.02 %
Max. mould temperature	65 - 93 °C
Injection speed	medium-fast

Processing Texts

Pre-drying	To avoid hydrolytic degradation during processing, CELANEX resins have to be dried to a moisture level equal to or less than 0.02%. Drying should be done in a dehumidifying hopper dryer capable of dewpoints <-40°F (-40°C) for 4 hours.
Longer pre-drying times/storage	d For subsequent storage of the material in a dryer until processed (<= 60hr) it is necessary to lower the temperature to 100°C.