

THERMX[®] TE3002

PCT

Thermx® TE3002 is a 30% glass fiber reinforced, flame retardant, black high performance polyester resin for injection molding.

Product information

Resin Identification Part Marking Code	PCT-GF30 >PCT-GF30<		ISO 1043 ISO 11469
Typical mechanical properties			
Tensile modulus Tensile stress at break, 5mm/min Tensile strain at break, 5mm/min Flexural modulus Flexural strength Charpy impact strength, 23°C Charpy impact strength, -30°C Charpy notched impact strength, 23°C Charpy notched impact strength, -30° Poisson's ratio [OT]: One time tested [C]: Calculated	1.2 10500 150 20 21 ^[07] C 7	MPa % MPa MPa kJ/m ² kJ/m ² kJ/m ²	ISO 527-1/-2 ISO 527-1/-2 ISO 527-1/-2 ISO 178 ISO 178 ISO 179/1eU ISO 179/1eU ISO 179/1eA ISO 179/1eA
Thermal properties			
Temperature of deflection under load,	1.8 MPa 240	°C	ISO 75-1/-2
Flammability			
Burning Behav. at thickness h Thickness tested UL recognition	V-0 0.79 yes	class mm	IEC 60695-11-10 IEC 60695-11-10 UL 94
Electrical properties Electric strength [OT]: One time tested	34 ^[OT]	kV/mm	IEC 60243-1
Physical/Other properties Density	1650	kg/m³	ISO 1183
Characteristics			
Processing	Injection Moulding		
Delivery form	Pellets		
Special characteristics	Flame retardant, Chemical resistant		

(+) **18816996168** Ponciplastics.com



THERMX[®] TE3002

Printed: 2025-05-30

Revised: 2024-04-16 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication as a promise or guarantee of specific properties of our groucts. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to he lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material inductions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for addi

© 2025 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC.

Page: 2 of 2