



THERMX® TE4005

PCT

Thermx® TE4005 NC010 is a 33% glass fiber/mineral reinforced polycyclohexylenedimethylene terephthalate resin developed for injection molding applications. It is specifically suitable for high performance demanding ignition applications. PRELIMINARY DATA

Product information

Resin Identification	PCT-(GF+MD)3	ISO 1043
	3	
Part Marking Code	>PCT-(GF+MD)33<	ISO 11469

Rheological properties

Moulding shrinkage, parallel	0.3 %	ISO 294-4, 2577
Moulding shrinkage, normal	0.5 %	ISO 294-4, 2577

Typical mechanical properties

Tensile modulus	9000	MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	110	MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	1.8	%	ISO 527-1/-2
Charpy impact strength, 23°C	40	kJ/m²	ISO 179/1eU
Poisson's ratio	0.34 ^[C]		

[C]: Calculated

Thermal properties

Melting temperature, 10°C/min	285 °C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	230 °C	ISO 75-1/-2

Electrical properties

Electric strength	46 kV/mm	IEC 60243-1
Comparative tracking index, 100 drops	600	IEC 60112

Physical/Other properties

Density	1450 kg/m ³	ISO 1183

Injection

Ejection temperature 233 °C

Characteristics

Processing Injection Moulding

Delivery form Pellets

Special characteristics Chemical resistant

Printed: 2025-05-30 Page: 1 of 2

Revised: 2024-05-15 Source: Celanese Materials Database

(+) **18816996168**Ponciplastics. com



THERMX® TE4005

PCT

Printed: 2025-05-30 Page: 2 of 2

Revised: 2024-05-15 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any e

© 2025 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC.