

Rynite® 530HTE BK503

THERMOPLASTIC POLYESTER RESIN

Rynite® 530HTE BK503 is a 30% glass reinforced modified polyethylene terephthalate resin with excellent high temperature dielectric properties

Product information

Resin Identification	PET-GF30	ISO 1043
Part Marking Code	>PET-GF30<	ISO 11469

Rheological properties

Moulding shrinkage, parallel	0.1 %	ISO 294-4, 2577
Moulding shrinkage, normal	0.6 %	ISO 294-4, 2577
Postmoulding shrinkage, normal, 48h at 80°C	0.45 %	ISO 294-4
Postmoulding shrinkage, parallel, 48h at 80°C	0.1 %	ISO 294-4

Typical mechanical properties

Tensile modulus	11000 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	160 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	1.9 %	ISO 527-1/-2
Compressive strength	230 MPa	ISO 604
Charpy impact strength, 23°C	42 kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	8.9 kJ/m ²	ISO 179/1eA
Hardness, Rockwell, R-scale	120	ISO 2039-2
Ball indentation hardness, H 961/30	221 MPa	ISO 2039-1
Poisson's ratio	0.34	

Thermal properties

Melting temperature, 10°C/min	252 °C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	90 °C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	230 °C	ISO 75-1/-2
Temperature of deflection under load, 0.45 MPa	251 °C	ISO 75-1/-2
Thermal conductivity, flow	0.29 W/(m K)	ISO 22007-2

Flammability

Glow Wire Flammability Index, 3.0mm	800 °C	IEC 60695-2-12
Glow Wire Ignition Temperature, 3.0mm	775 °C	IEC 60695-2-13
Glow Wire Temperature, No Flame, 1mm	750 °C	IEC 60335-1
Glow Wire Temperature, No Flame, 1.5mm	750 °C	IEC 60335-1
Glow Wire Temperature, No Flame, 2mm	750 °C	IEC 60335-1
Glow Wire Temperature, No Flame, 3mm	825 °C	IEC 60335-1
FMVSS Class	B	ISO 3795 (FMVSS 302)
Burning rate, Thickness 1 mm	<80 mm/min	ISO 3795 (FMVSS 302)

Rynite® 530HTE BK503

THERMOPLASTIC POLYESTER RESIN

Electrical properties

Relative permittivity, 100Hz	4.3	IEC 62631-2-1
Relative permittivity, 1MHz	3.8	IEC 62631-2-1
Dissipation factor, 100Hz	18 E-4	IEC 62631-2-1
Dissipation factor, 1MHz	146 E-4	IEC 62631-2-1
Volume resistivity	>1E13 Ohm.m	IEC 62631-3-1
Surface resistivity	1E14 Ohm	IEC 62631-3-2
Electric strength	35 kV/mm	IEC 60243-1
Comparative tracking index	200	IEC 60112
Electric Strength, Short Time, 23°C, 2mm	23 kV/mm	IEC 60243-1

Physical/Other properties

Water absorption, Immersion 24h	0.05 %	Sim. to ISO 62
Density	1590 kg/m³	ISO 1183

VDA Properties

Fogging, G-value (condensate)	0 mg	ISO 6452
-------------------------------	------	----------

Injection

Drying Recommended	yes
Drying Temperature	120 °C
Drying Time, Dehumidified Dryer	4 - 6 h
Processing Moisture Content	≤0.02 ^[1] %
Melt Temperature Optimum	285 °C
Min. melt temperature	280 °C
Max. melt temperature	300 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	140 °C
Min. mould temperature	120 °C
Max. mould temperature	140 ^[2] °C
Hold pressure range	≥80 MPa
Hold pressure time	4 s/mm
Back pressure	As low as possible MPa
Ejection temperature	170 °C

[1]: At levels above 0.02%, strength and toughness will decrease, even though parts may not exhibit surface defects.

[2]: (6mm - 1mm thickness)

Characteristics

Processing	Injection Moulding
------------	--------------------


Additional information

Injection molding	When lower mold temperatures are used, the initial warpage and shrinkage will be lower, but the surface appearance will be poorer and the dimensional change may be greater when parts are subsequently heated.
-------------------	---

Rynite® 530HTE BK503

THERMOPLASTIC POLYESTER RESIN


Stress-strain
(measured on Rynite® 530 NC010)



Rynite® 530HTE BK503

THERMOPLASTIC POLYESTER RESIN

Secant modulus-strain
(measured on Rynite® 530 NC010)



Printed: 2025-05-30

Page: 4 of 4

Revised: 2025-04-19 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

© 2025 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC.