

CELCON[®] F20-03HC LOF2

CELCON®

CELCON® F20-03HC LOF2 is a medium-viscosity grade for general injection molding. Suitable for injection molding application with heat resistance-improved feature.

Product information				
Resin Identification		POM		ISO 1043
Part Marking Code		>POM<		ISO 11469
Rheological properties				
Melt mass-flow rate			g/10min	ISO 1133
Melt mass-flow rate, Temperature		190		
Melt mass-flow rate, Load		2.16	•	
Moulding shrinkage, parallel		2.0	%	ISO 294-4, 2577
Typical mechanical properties				
Tensile stress at yield, 50mm/min		68	MPa	ISO 527-1/-2
Tensile strain at yield, 50mm/min		8	%	ISO 527-1/-2
Nominal strain at break		35	%	ISO 527-1/-2
Flexural modulus		2650		ISO 178
Flexural strength	_		MPa	ISO 178
Charpy notched impact strength, 23°C	2	6.5	kJ/m²	ISO 179/1eA
Thermal properties				
Melting temperature, 10°C/min		170	°C	ISO 11357-1/-3
Temperature of deflection under load,	1.8 MPa	100	°C	ISO 75-1/-2
Flammability				
Burning Behav. at thickness h		HB	class	IEC 60695-11-10
Thickness tested		3	mm	IEC 60695-11-10
Electrical properties				
Volume resistivity		1F12	Ohm.m	IEC 62631-3-1
Surface resistivity		1E16	-	IEC 62631-3-2
Electric strength			kV/mm	IEC 60243-1
Physical/Other properties				
Humidity absorption, 2mm		0.2	%	Sim. to ISO 62
Density			kg/m ³	ISO 1183
Characteristics				
Processing	Injection Moulding			
Delivery form	Pellets			

Printed: 2025-05-30





Page: 2 of 2

CELCON[®] F20-03HC LOF2

CELCON®

Automotive

OEM Hyundai STANDARD MS237-12 Type A ADDITIONAL INFORMATION Ulsan, Korea

Printed: 2025-05-30

Revised: 2025-01-23 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication as a promise or guarantee of specific properties of our groucts. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the

© 2025 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC.