

HOSTAFORM® C 9021 GV3/20

HOSTAFORM®

Chemical abbreviation according to ISO 1043-1: POM Molding compound ISO 29988- POM-K, M-GNR, 03-002, GB20 POM copolymer Injection molding type, reinforced with ca. 20 % glass spheres; high resistance to thermal and oxidative degradation. UL-registration in natural and a thickness more than 0.81 mm, in black and a thickness more than 1.5 mm as UL94 HB, temperature index UL 746 B for a thickness of 3 mm, electrical 105 °C, mechanical 95 °C (tensile impact) and 100 °C (tensile). Burning rate ISO 3795 and FMVSS 302 < 100 mm/min for a thickness more than 1 mm. Ranges of applications: For low-warpage molded parts with higher rigidity and hardness. FMVSS = Federal Motor Vehicle Safety Standard (USA) UL = Underwriters Laboratories (USA)

Product information

| | | |
|----------------------|-------|-----------|
| Resin Identification | POM | ISO 1043 |
| Part Marking Code | >POM< | ISO 11469 |

Rheological properties

| | | |
|------------------------------------|----------------------------|-----------------|
| Melt volume-flow rate | 8.5 cm ³ /10min | ISO 1133 |
| Temperature | 190 °C | |
| Load | 2.16 kg | |
| Moulding shrinkage range, parallel | 1.9 % | ISO 294-4, 2577 |
| Moulding shrinkage range, normal | 1.6 % | ISO 294-4, 2577 |

Typical mechanical properties

| | | |
|---------------------------------------|-----------------------|--------------|
| Tensile modulus | 3400 MPa | ISO 527-1/-2 |
| Tensile stress at yield, 50mm/min | 46 MPa | ISO 527-1/-2 |
| Tensile strain at yield, 50mm/min | 6.5 % | ISO 527-1/-2 |
| Nominal strain at break | 15 % | ISO 527-1/-2 |
| Flexural modulus | 3200 MPa | ISO 178 |
| Compressive stress at 1% strain | 26 MPa | ISO 604 |
| Tensile creep modulus, 1h | 3000 MPa | ISO 899-1 |
| Tensile creep modulus, 1000h | 1700 MPa | ISO 899-1 |
| Charpy impact strength, 23°C | 50 kJ/m ² | ISO 179/1eU |
| Charpy impact strength, -30°C | 50 kJ/m ² | ISO 179/1eU |
| Charpy notched impact strength, 23°C | 3.5 kJ/m ² | ISO 179/1eA |
| Charpy notched impact strength, -30°C | 3.5 kJ/m ² | ISO 179/1eA |
| Ball indentation hardness, H 358/30 | 164 MPa | ISO 2039-1 |
| Poisson's ratio | 0.37 ^[C] | |

[C]: Calculated

Thermal properties

| | | |
|--|-----------|----------------|
| Melting temperature, 10°C/min | 166 °C | ISO 11357-1/-3 |
| Temperature of deflection under load, 1.8 MPa | 110 °C | ISO 75-1/-2 |
| Coefficient of linear thermal expansion (CLTE), parallel | 100 E-6/K | ISO 11359-1/-2 |

Flammability

| | | |
|--------------------------------------|----------|-----------------|
| Burning Behav. at 1.5mm nom. thickn. | HB class | IEC 60695-11-10 |
| Thickness tested | 1.5 mm | IEC 60695-11-10 |
| Burning Behav. at thickness h | HB class | IEC 60695-11-10 |
| Thickness tested | 0.81 mm | IEC 60695-11-10 |
| UL recognition | yes | UL 94 |

HOSTAFORM® C 9021 GV3/20

HOSTAFORM®

Electrical properties

| | | |
|------------------------------|------------|---------------|
| Relative permittivity, 100Hz | 4.5 | IEC 62631-2-1 |
| Relative permittivity, 1MHz | 4.2 | IEC 62631-2-1 |
| Dissipation factor, 100Hz | 200 E-4 | IEC 62631-2-1 |
| Dissipation factor, 1MHz | 70 E-4 | IEC 62631-2-1 |
| Volume resistivity | 1E12 Ohm.m | IEC 62631-3-1 |
| Surface resistivity | 1E14 Ohm | IEC 62631-3-2 |
| Electric strength | 35 kV/mm | IEC 60243-1 |
| Comparative tracking index | 600 | IEC 60112 |

Physical/Other properties

| | | |
|--------------------------|------------|----------------|
| Humidity absorption, 2mm | 0.15 % | Sim. to ISO 62 |
| Water absorption, 2mm | 0.8 % | Sim. to ISO 62 |
| Density | 1530 kg/m³ | ISO 1183 |

Injection

| | |
|---------------------------------|--------------|
| Drying Recommended | no |
| Drying Temperature | 100 °C |
| Drying Time, Dehumidified Dryer | 3 - 4 h |
| Processing Moisture Content | ≤0.2 % |
| Melt Temperature Optimum | 200 °C |
| Min. melt temperature | 190 °C |
| Max. melt temperature | 210 °C |
| Screw tangential speed | ≤0.3 m/s |
| Mold Temperature Optimum | 100 °C |
| Min. mould temperature | 80 °C |
| Max. mould temperature | 120 °C |
| Hold pressure range | 60 - 120 MPa |
| Back pressure | 2 MPa |

Characteristics

| | |
|-------------------------|--------------------|
| Processing | Injection Moulding |
| Delivery form | Pellets |
| Additives | Release agent |
| Special characteristics | Low Warpage |

Additional information

Injection molding

Preprocessing

General drying is not necessary due to low moisture absorption of the resin.

In case of bad storage conditions (water contact or condensed water) the use of a recirculating air dryer (100 to 120 °C / max. 40 mm layer / 3 to 6 hours) is recommended.

HOSTAFORM® C 9021 GV3/20

HOSTAFORM®

Max. Water content 0,2 %

Processing

Standard injection moulding machines with three phase (15 to 25 D) plasticating screws will fit.

Postprocessing

Conditioning e.g. moisturizing is not necessary.

Pre-Drying

Drying is not normally required. If material has come in contact with moisture through improper storage or handling or through regrind use, drying may be necessary to prevent splay and odor problems.

Storage

The product can then be stored in standard conditions until processed.

Processing Notes

Automotive

OEM

Bosch

Bosch

Continental

STANDARD

N28 BN22-X014

N28 BN22-X014

TST N 055 54.15

ADDITIONAL INFORMATION


Natural

Black

HOSTAFORM® C 9021 GV3/20

HOSTAFORM®


Viscosity-shear rate



HOSTAFORM® C 9021 GV3/20

HOSTAFORM®


Shearstress-shear rate



HOSTAFORM® C 9021 GV3/20

HOSTAFORM®


Stress-strain



HOSTAFORM® C 9021 GV3/20

HOSTAFORM®

Secant modulus-strain



Printed: 2025-05-30

Page: 7 of 7

Revised: 2024-07-16 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

© 2025 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC.