

# HOSTAFORM® LM270Z XAP®2

## HOSTAFORM®

Hostaform® acetal copolymer grade LX270Z XAP®2 is a UV stabilized material available in a range of molded in metallic colors generally for automotive interior applications and is a higher flow grade than LX90Z. In addition, Hostaform® LX270Z XAP®2 has lower volatile emissions as required for some automotive interiors. Flow properties of this grade is based upon the uncolored acetal copolymer and flow testing does not reflect how it actually flows. Besides material, optimal finish for specialty metallic parts is dependent on proper drying, gate design, knit line locations, and special processing. Please contact Celanese Technical Service for assistance with your application.

### Product information

Resin Identification	POM	ISO 1043
Part Marking Code	>POM<	ISO 11469

### Rheological properties

Melt volume-flow rate	24 cm <sup>3</sup> /10min	ISO 1133
Temperature	190 °C	
Load	2.16 kg	

### Typical mechanical properties

Tensile modulus	2600 MPa	ISO 527-1/-2
Tensile stress at yield, 50mm/min	62 MPa	ISO 527-1/-2
Tensile strain at yield, 50mm/min	7.5 %	ISO 527-1/-2
Charpy notched impact strength, 23 °C	5.5 kJ/m <sup>2</sup>	ISO 179/1eA
Poisson's ratio	0.38 <sup>[C]</sup>	

[C]: Calculated

### Thermal properties

Melting temperature, 10 °C/min	164 °C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	100 °C	ISO 75-1/-2
Coefficient of linear thermal expansion (CLTE), parallel	110 E-6/K	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	110 E-6/K	ISO 11359-1/-2

### Physical/Other properties

Humidity absorption, 2mm	0.2 %	Sim. to ISO 62
Water absorption, 2mm	0.65 %	Sim. to ISO 62
Density	1410 kg/m <sup>3</sup>	ISO 1183

### Injection

Drying Recommended	no
Drying Temperature	100 °C
Drying Time, Dehumidified Dryer	3 - 4 h
Processing Moisture Content	≤0.2 %
Melt Temperature Optimum	190 °C
Min. melt temperature	180 °C
Max. melt temperature	200 °C
Screw tangential speed	≤0.3 m/s
Mold Temperature Optimum	100 °C
Min. mould temperature	80 °C

# HOSTAFORM® LM270Z XAP®2

## HOSTAFORM®

Max. mould temperature	120 °C
Hold pressure range	60 - 120 MPa
Back pressure	4 MPa

### Characteristics

Processing	Injection Moulding
Delivery form	Granules
Special characteristics	Light stabilised or stable to light, U.V. stabilised or stable to weather, Laser Markable, High Flow, Low emissions

### Additional information

Injection molding

### Preprocessing

To achieve low emission values pre drying using a recirculating air dryer (100 to 120 °C / max. 40 mm layer / 3 to 6 hours) is recommended.

Max. Water content 0,1 %

### Processing

Standard injection moulding machines with three phase (15 to 25 D) plasticating screws will fit.

Melt temperature 180-190 °C  
Mould temperature 60-120 °C

### Postprocessing

Conditioning e.g. moisturizing is not necessary.

Processing Notes

### Pre-Drying

recommended

### Automotive

OEM  
VW Group

STANDARD  
TL 524 76

ADDITIONAL INFORMATION  
10/9222 Black

# HOSTAFORM® LM270Z XAP®2

## HOSTAFORM®

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

© 2025 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC.