

HOSTAFORM® UV25Z XAP®2

UV resistant and low emission - automotive, improved toughness

HOSTAFORM® UV25Z XAP2 is a nominal 2.5 melt flow rate acetal copolymer which has been specially stabilized to prevent discoloration and deterioration of mechanical properties from ultraviolet light exposure. The material is available in precolored black or colors, with reduced emissions especially for automotive interior application. Emission according to VDA 275 < 5 mg/kg (natural grades) Emission according to VDA 275 < 5 mg/kg (colored grades).

Rheological properties

Melt mass-flow rate	2.3 g/10min	ISO 1133
Melt mass-flow rate, Temperature	190 °C	
Melt mass-flow rate, Load	2.16 kg	

Typical mechanical properties

Tensile Modulus	2400 MPa	ISO 527-1/-2
Yield stress, 50mm/min	60 MPa	ISO 527-1/-2
Yield strain, 50mm/min	10 %	ISO 527-1/-2
Charpy notched impact strength, 23°C	8 kJ/m²	ISO 179/1eA

Thermal properties

Melting temperature, 10°C/min	165 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	90 °C	ISO 75-1/-2

Other properties

Density	1400 kg/m³	ISO 1183
---------	------------	----------

Injection

Drying Temperature	100 - 120 °C
Drying Time, Dehumidified Dryer	3 - 4 h
Processing Moisture Content	0.15 %
Screw tangential speed	0.2 - 0.21 m/s
Max. mould temperature	80 - 120 °C
Back pressure	4 MPa
Injection speed	slow-medium

Additional information

Injection molding	Standard injection moulding machines with three phase (15 to 25 D) plasticating screws will fit.
-------------------	--

Processing Texts

Longer pre-drying times/storage	The product can then be stored in standard conditions until processed.
---------------------------------	--

Injection molding	Standard injection moulding machines with three phase (15 to 25 D) plasticating screws will fit.
-------------------	--

HOSTAFORM® UV25Z XAP®2

Injection molding Preprocessing

HOSTAFORM® UV25Z XAP®2

To achieve low emission values pre drying using a recirculating air dryer (100 to 120 °C / max. 40 mm layer / 3 to 6 hours) is recommended.

Max. Water content 0,1 %

Injection molding Postprocessing

Postprocessing conditioning and moisturizing are not required. It may be necessary to fixture large or complicated parts with varying wall thickness to prevent warpage while cooling to ambient temperature.