

HOSTAFORM® UV90Z XAP®2

UV resistance, low emission

Hostaform® acetal copolymer grade UV90Z XAP®2 is a UV stabilized material available in a range of colors generally for automotive interior applications. In addition, Hostaform® UV90Z XAP®2 has lower emissions as required for some automotive interiors. Low Emission Performance [VDA-275] <5 PPM

Rheological properties

Melt volume-flow rate	8 cm ³ /10min	ISO 1133
Temperature	190 °C	
Load	2.16 kg	
Moulding shrinkage range, parallel	2.0 %	ISO 294-4, 2577
Moulding shrinkage range, normal	1.7 %	ISO 294-4, 2577

Typical mechanical properties

Tensile Modulus	2650 MPa	ISO 527-1/-2
Yield stress, 50mm/min	64 MPa	ISO 527-1/-2
Yield strain, 50mm/min	9 %	ISO 527-1/-2
Charpy notched impact strength, 23°C	6 kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	5 kJ/m ²	ISO 179/1eA
Hardness, Rockwell, M-scale	83	ISO 2039-2

Thermal properties

Melting temperature, 10°C/min	167 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	90 °C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	154 °C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	90 E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	110 E-6/K	ISO 11359-1/-2

Other properties


Density	1400 kg/m ³	ISO 1183
---------	------------------------	----------

Injection

Drying Temperature	100 - 120 °C
Drying Time, Dehumidified Dryer	3 - 4 h
Max. mould temperature	80 - 120 °C
Back pressure	4 MPa
Injection speed	slow-medium


HOSTAFORM® UV90Z XAP®2

Stress-strain



HOSTAFORM® UV90Z XAP®2

Secant modulus-strain



HOSTAFORM® UV90Z XAP®2

Processing Texts

Pre-drying

Drying is recommended to obtain optimum emission performance. If material contacts moisture through improper storage or handling, drying may be necessary to prevent splay and odor issues.

Other Approvals

Other Approvals

OEM	Specification	Additional Information
Stellantis - Chrysler	CPN 1758	100% color match
Ford	WSS-M4D840-B1	
Geely	Q/JLY J7110235B	2018
GM	GMW16924P-POM-C2	
Li Auto	Q/LiA5310020	2021 (V2)
VW Group	TL 524 76	Natural