

KEPITAL® FL2010

A 10% PTFE powder filled grade for general injection molding

KEPITAL FL2010 is a 10% PTFE powder filled grade, good for general injection molding. It is suitable for parts that are required of low wear and friction.

Rheological properties

Moulding shrinkage range, parallel	2.0 %	ISO 294-4, 2577
------------------------------------	-------	-----------------

Typical mechanical properties

Yield stress, 50mm/min	55 MPa	ISO 527-1/-2
Nominal strain at break	14 %	ISO 527-1/-2
Flexural Modulus	2400 MPa	ISO 178
Flexural Strength	80 MPa	ISO 178
Charpy notched impact strength, 23°C	3 kJ/m ²	ISO 179/1eA

Thermal properties

Melting temperature, 10°C/min	165 °C	ISO 11357-1/-3
-------------------------------	--------	----------------

Electrical properties

Volume resistivity	>1E14 Ohm.m	IEC 62631-3-1
Surface resistivity	>1E16 Ohm	IEC 62631-3-2

Other properties

Humidity absorption, 2mm	0.19 %	Sim. to ISO 62
Density	1450 kg/m ³	ISO 1183
