

KEPITAL® NX-20 LOF

A emission optimized, friction and wear-resistance grade for general injection molding
A friction and wear resistance grade for general injection molding. Emission optimized.

Rheological properties

Moulding shrinkage range, parallel	2.0 %	ISO 294-4, 2577
------------------------------------	-------	-----------------

Typical mechanical properties

Yield stress, 50mm/min	55 MPa	ISO 527-1/-2
Nominal strain at break	18 %	ISO 527-1/-2
Flexural Modulus	2350 MPa	ISO 178
Flexural Strength	76 MPa	ISO 178
Charpy notched impact strength, 23°C	3.4 kJ/m ²	ISO 179/1eA

Thermal properties

Melting temperature, 10°C/min	165 °C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	90 °C	ISO 75-1/-2

Electrical properties

Volume resistivity	>1E12 Ohm.m	IEC 62631-3-1
Surface resistivity	>1E16 Ohm	IEC 62631-3-2

Other properties

Density	1380 kg/m ³	ISO 1183
---------	------------------------	----------
