

POLIFOR® C25 AS - PP

Description

Polypropylene, copolymer, unfilled.

Physical properties	Value	Unit	Test Standard
Density	910	kg/m ³	ISO 1183
Melt flow rate, MFR	20	g/10min	ISO 1133
MFR temperature	230	°C	ISO 1133
MFR load	2.16	kg	ISO 1133

Mechanical properties	Value	Unit	Test Standard
Tensile modulus	1300	MPa	ISO 527-2/1A
Tensile stress at yield, 50mm/min	25	MPa	ISO 527-2/1A
Tensile strain at break, 50mm/min	>35	%	ISO 527-2/1A
Flexural modulus, 23°C	1300	MPa	ISO 178
Charpy impact strength, 23°C	>80	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	6	kJ/m ²	ISO 179/1eA
Izod impact notched, 23°C	6	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
Vicat softening temperature, 50°C/h 50N	70	°C	ISO 306
Flammability @ 1.6mm nom. thickn.	HB	class	UL 94

Typical injection moulding processing conditions

Pre Drying	Value	Unit	Test Standard
Drying time	2 - 3	h	-
Drying temperature	80 - 100	°C	-
Temperature	Value	Unit	Test Standard
Zone1 temperature	190 - 210	°C	-
Zone2 temperature	210 - 230	°C	-
Zone3 temperature	220 - 240	°C	-
Nozzle temperature	230 - 250	°C	-
Mold temperature	30 - 60	°C	-

Characteristics

Special Characteristics	Processing
Anti-static	Injection molding

Product Categories

Unfilled