

**POLIFOR® CL12 GF/15 V0-H - PP****Description**

Polypropylene, copolymer, 15% glass fiber reinforced, chemically coupled, heat stabilised, UL listed V0

<b>Physical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	84.9	lb/ft³	ISO 1183
Melt flow rate, MFR	6.5	g/10min	ISO 1133
MFR temperature	446	°F	ISO 1133
MFR load	4.76	lb	ISO 1133
<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Tensile stress at break, 5mm/min	6530	psi	ISO 527-1, -2
Flexural modulus, 23°C	653000	psi	ISO 178
Charpy impact strength, 23°C	21.4	ft-lb/in²	ISO 179/1eU
Charpy notched impact strength, 23°C	5.23	ft-lb/in²	ISO 179/1eA
Izod impact notched, 23°C	5.23	ft-lb/in²	ISO 180/1A
<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Flammability @3.2mm nom. thickn.	V-0	class	UL 94
Flammability at thickness h thickness tested (h)	V-0 0.0591	class in	UL 94 UL 94
UL recognition (h)	UL	-	UL 94

**Typical injection moulding processing conditions**

<b>Pre Drying</b>	<b>Value</b>	<b>Unit</b>
Drying time	2 - 3	h
Drying temperature	176 - 212	°F
<b>Temperature</b>	<b>Value</b>	<b>Unit</b>
Zone1 temperature	374 - 410	°F
Zone2 temperature	392 - 428	°F
Zone3 temperature	410 - 446	°F
Nozzle temperature	410 - 446	°F
Mold temperature	122 - 176	°F

**Other text information****Longer pre-drying times/storage**

This product should be stored in a covered facility and kept away from moisture and heat.

**Characteristics**

<b>Special Characteristics</b>	Flame retardant, Heat resistant
<b>Product Categories</b>	Glass reinforced
<b>Processing</b>	Injection molding
<b>Additives</b>	Flame retarding agent