

POLIFOR® E30 TR/20 UV

Polypropylene copolymer, impact modified, 20% talc filled, UV stabilised.

Rheological properties

Melt mass-flow rate	20 g/10min	ISO 1133
Melt mass-flow rate, Temperature	230 °C	
Melt mass-flow rate, Load	2.16 kg	

Typical mechanical properties

Yield stress, 50mm/min	15 MPa	ISO 527-1/-2
Strain at break, 50mm/min	30 %	ISO 527-1/-2
Flexural Modulus	1650 MPa	ISO 178
Charpy impact strength, 23°C	>100 kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	50 kJ/m ²	ISO 179/1eA
Izod notched impact strength, 23°C	45 kJ/m ²	ISO 180/1A

Thermal properties

Temp. of deflection under load, 1.8 MPa	48 °C	ISO 75-1/-2
---	-------	-------------

Other properties

Density	1050 kg/m ³	ISO 1183
---------	------------------------	----------

Injection

Drying Temperature	80 - 100 °C
Drying Time, Dehumidified Dryer	2 - 3 h
Max. mould temperature	30 - 60 °C

Characteristics

Additives	Mineral Filler
-----------	----------------

Processing Texts

Longer pre-drying times/storage	This product should be stored in a covered facility and kept away from moisture and heat.
---------------------------------	---