

TALCOPRENE® 1040TL

Polypropylene, homopolymer, 40% mineral filled.

Typical mechanical properties

Tensile Modulus	3900 MPa	ISO 527-1/-2
Stress at break, 5mm/min	27 MPa	ISO 527-1/-2
Flexural Modulus	3800 MPa	ISO 178
Flexural Strength	44 MPa	ISO 178
Izod notched impact strength, 23°C	2.1 kJ/m ²	ISO 180/1A

Flammability

Burning Behav. at 1.5mm nom. thickn.	HB class	UL 94
Burning Behav. at thickness h	HB class	UL 94

Other properties

Density	1290 kg/m ³	ISO 1183
---------	------------------------	----------

Injection

Drying Temperature	80 - 100 °C
Drying Time, Dehumidified Dryer	2 - 3 h
Max. mould temperature	30 - 60 °C

Characteristics

Additives	Mineral Filler
-----------	----------------

Processing Texts

Longer pre-drying times/storage	This product should be stored in a covered facility and kept away from moisture and heat.
---------------------------------	---