

# TALCOPRENE® 340TL

## TALCOPRENE®

Polypropylene, homopolymer, mineral filled, high heat stabilization.

### Product information

Resin Identification	PP-T37	ISO 1043
Part Marking Code	>PP-T37<	ISO 11469

### Rheological properties

Melt mass-flow rate	4.5 g/10min	ISO 1133
Melt mass-flow rate, Temperature	230 °C	
Melt mass-flow rate, Load	2.16 kg	

### Typical mechanical properties

Tensile modulus	3400 MPa	ISO 527-1/-2
Tensile stress at yield, 50mm/min	29 MPa	ISO 527-1/-2
Tensile strain at yield, 50mm/min	3 %	ISO 527-1/-2
Tensile strain at break, 50mm/min	12 %	ISO 527-1/-2
Flexural modulus	3500 MPa	ISO 178
Flexural strength	45 MPa	ISO 178
Charpy impact strength, 23 °C	33 kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23 °C	2.6 kJ/m <sup>2</sup>	ISO 179/1eA
Poisson's ratio	0.37 <sup>[C]</sup>	

[C]: Calculated

### Thermal properties

Temperature of deflection under load, 1.8 MPa	72 °C	ISO 75-1/-2
Vicat softening temperature, 50 °C/h 50N	95 °C	ISO 306

### Flammability

Burning Behav. at 1.5mm nom. thickn.	HB class	IEC 60695-11-10
Burning Behav. at thickness h	HB class	IEC 60695-11-10
Thickness tested	3.2 mm	IEC 60695-11-10

### Physical/Other properties

Density	1240 kg/m <sup>3</sup>	ISO 1183
---------	------------------------	----------

### Characteristics

Processing	Injection Moulding
Additives	Mineral Filler
Special characteristics	Heat stabilised or stable to heat

### Additional information

Processing Notes

### Storage

This product should be stored in a covered facility and kept away from moisture and heat.

# TALCOPRENE® 340TL

## TALCOPRENE®

Printed: 2025-05-30

Page: 2 of 2

Revised: 2024-01-23 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design, processing conditions and environmental exposure. Other than those products expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication should not be construed as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials to the lowest practical limits in view of possible adverse effects. To the extent that any hazards may have been mentioned in this publication, we neither suggest nor guarantee that such hazards are the only ones that exist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the manufacturer's current instructions for handling each material they use, and entrust the handling of such material to adequately trained personnel only. Please call the telephone numbers listed for additional technical information. Call Customer Services for the appropriate Materials Safety Data Sheets (MSDS) before attempting to process our products.

© 2025 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC.