

TECNOPRENE® HKM24LE

Polypropylene, homopolymer, 20% talc filled, 10% glass fiber reinforced, chemically coupled, low emission.

Typical mechanical properties

Tensile Modulus	4800 MPa	ISO 527-1/-2
Stress at break, 5mm/min	54 MPa	ISO 527-1/-2
Strain at break, 5mm/min	3 %	ISO 527-1/-2
Flexural Modulus	4400 MPa	ISO 178
Flexural Strength	90 MPa	ISO 178
Charpy notched impact strength, 23°C	5 kJ/m ²	ISO 179/1eA
Izod notched impact strength, 23°C	5.8 kJ/m ²	ISO 180/1A

Thermal properties

Temp. of deflection under load, 1.8 MPa	132 °C	ISO 75-1/-2
---	--------	-------------

Flammability

Burning Behav. at 1.5mm nom. thickn.	HB class	UL 94
Burning Behav. at thickness h	HB class	UL 94

Other properties

Density	1130 kg/m ³	ISO 1183
---------	------------------------	----------

Injection

Drying Temperature	80 - 100 °C
Drying Time, Dehumidified Dryer	2 - 3 h
Max. mould temperature	50 - 80 °C

Processing Texts

Longer pre-drying times/storage	This product should be stored in a covered facility and kept away from moisture and heat.
---------------------------------	---

Other Approvals

Other Approvals	<table><tr><td>OEM</td><td>Specification</td></tr><tr><td>VW Group</td><td>VW44045</td></tr></table>	OEM	Specification	VW Group	VW44045
OEM	Specification				
VW Group	VW44045				