

# SOFPRENE® 52019TA85 GRIGIO

## SOFPRENE®

### Product information

Resin Identification	SBS	ISO 1043
Part Marking Code	>SBS<	ISO 11469

### Rheological properties

Melt mass-flow rate	10 g/10min	ISO 1133
Melt mass-flow rate, Temperature	190 °C	
Melt mass-flow rate, Load	5 kg	

### Typical mechanical properties

Stress at break	8.2 MPa	ISO 527-1/-2 or ISO 37
Elongation at break, perpendicular	670 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	86	ISO 48-4 / ISO 868
Tear strength, normal	45 kN/m	ISO 34-1

### Physical/Other properties

Density	917 kg/m <sup>3</sup>	ISO 1183
---------	-----------------------	----------

### Characteristics

Processing	Injection Moulding
------------	--------------------

### Additional information

Injection molding

### Processing

Please note that the suggested temperatures are estimations. The actual desired temperatures can vary based on the molding machine design.

Processing Notes

### Storage

The material must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.