



## SOFPRENE<sup>®</sup> 540200A66 NEUTRO SOFPRENE®

## Product information

Resin Identification	SBS >SBS<	-	ISO 1043 ISO 11469
Part Marking Code	>000<	5	150 11469
Typical mechanical properties			
Tensile stress at 100% elongation	1.8	3 MPa	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	2.7	7 MPa	ISO 527-1/-2 or ISO 37
Stress at break	4.2	2 MPa	ISO 527-1/-2 or ISO 37
Elongation at break, perpendicular	650	) %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	67	7	ISO 48-4 / ISO 868
Tear strength, normal	26	6 kN/m	ISO 34-1
Physical/Other properties			
Density	1050	) kg/m³	ISO 1183

Printed: 2025-05-30

Revised: 2024-01-23 Source: Celanese Materials Database

NOTICE TO USERS: Values shown are based on testing of laboratory test specimens and represent data that fall within the standard range of properties for natural material. These values alone do not represent a sufficient basis for any part design and are not intended for use in establishing maximum, minimum, or ranges of values for specification purposes. Colourants or other additives may cause significant variations in data values. Properties of moulded parts can be influenced by a wide variety of factors including, but not limited to, material selection, additives, part design not intended for use in medical or dental implants. Regardless of any such product expressly identified as medical grade (including by MT® product designation or otherwise), Celanese's products are not intended for use in medical or dental implants. Regardless of any such product designation, any determination of the suitability of a particular material and part design for any use contemplated by the users and the manner of such use is the sole responsibility of the users, who must assure themselves that the material as subsequently processed meets the needs of their particular product or use. To the best of our knowledge, the information contained in this publication is accurate; however, we do not assume any liability whatsoever for the accuracy and completeness of such information. The information contained in this publication as a promise or guarantee of specific properties of our products. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of the materials mentioned in this publication. Moreover, there is a need to reduce human exposure to many materials the lowest that texist. We recommend that persons intending to rely on any recommendation or to use any equipment, processing technique or material mentioned in this publication should satisfy themselves that they can meet all applicable safety and health standards. We strongly recommend that users seek and adhere to the m

© 2025 Celanese or its affiliates. All rights reserved. Celanese®, registered C-ball design and all other trademarks identified herein with ®, TM, SM, unless otherwise noted, are trademarks of Celanese or its affiliates. Fortron is a registered trademark of Fortron Industries LLC.

Page: 1 of 1