

(+) 18816996168

Ponciplastics.com



# SOPRENE® 540500A60 NEUTRO

## Typical mechanical properties

Stress at 100% elongation	247 psi	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	363 psi	ISO 527-1/-2 or ISO 37
Stress at break	566 psi	ISO 527-1/-2 or ISO 37
Elongation at break	660 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	60	ISO 48-4 / ISO 868
Tear strength, normal	143 lb/in	ISO 34-1

## Other properties

Density	8 lb/gal	ISO 1183
---------	----------	----------

## Injection

Max. mould temperature	68 - 104 °F
------------------------	-------------